



Received: 09-05-2023
Accepted: 19-06-2023

ISSN: 2583-049X

Radioactivity: Shielding materials A review

¹Lubna A Alasadi, ²Entesser Farhan Salman

¹Department of Physics, Faculty of Science, University of Kufa, Najaf, Iraq

²Department of Physics, University of Babylon, Hillah, Iraq

Corresponding Author: **Lubna A Alasadi**

Abstract

When the rays pass through an absorbing medium such as the human body or any other organism, part of the energy of these rays is transferred to this medium. The amount of energy transferred, even in small proportions, may constitute biological damage. To reduce the risk, workers in the radiation field wear arm coats made of protective rubber. To protect them from radiation. Attenuation or shielding of gamma radiation is an important component of radiation, Safety programs aiming to reduce personnel exposure to

ionizing Radiation Attenuation data for use of shielding materials is commonly available in many resources such as lead and polymer composites. Polymers are high molecular weight compounds composed of units called monomers. Numerous molecules are regularly attached to each other by chemical bonds and form polymers. Polymers are used in many areas such as building materials, adhesives, electronic tool parts, insulating materials, metal materials, insulation materials, and textile and paper industries.

Keywords: Shielding Materials, Attenuation Coefficient, Radiation, Gamma-ray, X-ray

Introduction

The continuance of advances in nuclear technology led to make the radiation sources' interposition in many relevant fields such as the cultivation industry medicine nuclear power cohort and scientific research ^[1]. So nuclear shields are used to decrease the exposure to nuclear radiation and their secondary interactions with the material and to reduce the effects on human tissue ^[2]. Most of these shields are made from different types of materials depending on the energy type of radiation accessibility of the shielding material ^[3]. The polymer-based composites such as polyethylene polystyrene and epoxy have been selected in the field of radiation protection ^[4]. In recent years composite materials are employed in gamma ray shielding and showed good efficiency in this field Composite materials are multiphase materials that are obtained by an artificial combination of different materials so as to attain properties that the individual components by themselves cannot attain ^[5].

Gamma-ray

High-energy electromagnetic radiation is typically emitted from the atomic nucleus during nuclear decay processes. From the properties, gamma rays: Electrically neutral, Travel with the velocity of light. Penetration power is very large. It is about a hundred times larger than that of alpha.

Gamma-ray Produce feeble fluorescence Travel at the speed of light. Could only be stopped by a thick sheet of lead, steel, concrete, or several meters of water. Cobalt-60, caesium-137, zinc-65, and radium-22 are gamma emitters ^[6].

X-ray

Fundamentally the same as gamma rays, but originating from electrons outside the atomic nucleus. Some resources may also distinguish gamma rays and x-rays based on energy. They have a shorter wavelength of the electromagnetic spectrum and require high voltage to produce X-Rays. They are used to capture human skeleton defects. They travel in a straight line and do not carry an electric charge with them ^[7-8].

α -particle

Is emitted during the decay process. Such nuclei have a high proton-to-neutron ratio. α -particles are quite stable in their configuration with two protons and two neutrons. Protons to neutron ratio are reduced in the parent nucleus decay by altering the Z. So the parent and the daughter atoms are chemically different elements ^[9].

The capacity of the α -particle to penetrate materials is not very great, it usually penetrates no more than a few centimeters in air and is absorbed by a relatively small thickness of paper or human skin. However, because of their speed and size, they are

capable of ionizing a large number of atoms over a very short range of penetration. This makes them relatively harmless for most sources that are about a meter or more away, as the radiation is easily absorbed by the air. But if the radiation sources are close to sensitive organs α -particle radiation is extremely dangerous^[10].

β -particles

Beta-particle radiation consists of fast-moving electrons. Every β -particle carries either one negative or one positive electronic charge ($\pm 1.6 \times 10^{-19}$ coulomb: -e, +e). They are affected by electric and magnetic fields. The speed depends on the source, but it can be up to 90% of the speed of light. β particles can penetrate up to 1 m of air. They are stopped by a few millimeters of aluminum or Perspex. Their ionizing capacity is much less than that of α -radiation. They are very dangerous if ingested^[11].

Interaction of radiation with the material

The ways in which the rays interact with the material vary depending on the type, extent, and energy of these rays. In our subject, we discuss the gamma's interaction with the X-ray material.

A-Photoelectric effect

The complete transfer of energy from a gamma ray photon to an atomic electron of the shielding material. Photoelectric absorption is more common for lower energy gamma radiation (<500 keV) and for shielding materials constructed from high atomic number elements, such as tungsten, lead, and bismuth^[12].

B-Compton scattering

The transfer of part of the energy of a gamma-ray photon to an atomic electron of the shielding material. After undergoing Compton scattering, the gamma photon may undergo further scattering or absorption interactions with the shielding material and/or emerge from the shielding material with diminished energy. Compton scattering is predominant at relatively high gamma energies (500-1500 keV) and for shielding constructed from low atomic weight materials^[13].

C-Pair production

An interaction of a gamma ray photon with the nucleus of an atom results in the creation of a beta particle and a positron. The positron then undergoes an annihilation reaction with an electron to produce two 511 keV gamma rays. The incident gamma radiation must have a minimum energy of 1022 keV to undergo pair production. Pair production becomes an important attenuation interaction for very high energy radiation (>1500 KeV)^[14].

Attenuation coefficient

A magnitude that describes how simply electromagnetic radiation enters a material. The coefficient of attenuation (μ) can be represented by two units^[15]:

1- When measuring the thickness of the material (x) in cm, the calculated attenuation coefficient will be in units (cm^{-1}) called the total linear attenuation coefficient (μ) and the total linear attenuation coefficient depends on the energy of the falling photon, the atomic number (z) of the attenuated medium and the mean density (ρ).

2- When the thickness of the attenuated medium (x) is in mass units per unit area (g/cm^2). The attenuation coefficient

and the material density can be used to estimate the transmission of gamma radiation through a chosen thickness of shielding material or the thickness of a shielding material required to achieve a desired level of attenuation. Gamma attenuation coefficients are inversely dependent on gamma energy and directly proportional to the atomic number of the element from which the shielding material is constructed. It is normal when the rays pass in a certain material, the intensity of these rays will decrease and lose part of its energy as a result of losing it due to absorption by the material.

The special thickness that attenuates the beam to 50% is called the half-value layer or^[16].

$$\text{HVL} = x_b = \frac{\ln 2}{\mu} = 0.693/\mu \quad (1)$$

$$N = N_0 e^{-\mu x} \quad (2)$$

For shielding materials where published data isn't available, attenuation can be estimated through calculation. The attenuation of gamma radiation (shielding) can be described by the following equation:

$$I = I_0 e^{-\mu \rho t} \quad (3)$$

Where I = intensity after shielding, I_0 = incident intensity, μ = mass absorption coefficient (cm^2/g), ρ : density of the shielding material (g/cm^3), and t = physical thickness of the shielding material (cm). A plot of the total mass attenuation coefficient vs. Absorption coefficient ($\mu_0 \mu_{\text{total}}$) is actually the sum of the attenuation coefficients of photoelectric absorption, Compton scattering, and any other mechanism that is important for a given gamma energy^[16]:

$$\mu_{\text{total}} = \mu_{\text{photo}} + \mu_{\text{compton}} + \mu_{\text{pair-production}} \quad (4)$$

Table 1: Physical Properties of Shielding Materials

Material	Density(g/cm^3)	Material	Density(g/cm^3)
Water	1.00	TFlex®-Fe	2.8
Aluminum	2.70	TFlex®-50	3.8
Iron	7.86	TFlex®-Bi	4.7
Copper	8.96	Flex®-W	7.2
Bismuth	9.8	-	-
Lead	11.34	-	-
Tungsten	19.3	-	-

Polymer composites for gamma-radiation shielding

Special clothing has been used to protect medical personnel, doctors and nurses, and their patients, to protect against direct and secondary radiation during diagnostic imaging, resonance imaging, or scans in hospitals, clinics, and dental offices. Use lead to protect against radiation. However, technological advances in radiation shielding materials have led to the production of two alternative materials, the lead-free radiation shield material. And lead compounds and nanomaterials or nano-lead. Polymers are substances containing a large number of structural units joined by the same type of linkage. These substances often form a chain-like structure. It has been approximately 60 years since researchers first began exposing polymeric materials to ionizing radiations, and today, a substantial commercial industry is in place based on the processing of polymers

with radiation. Polymers are of low atomic number and low density and thus lightweight materials. Polymers possess high durability, and they are tough. Also, they are cost-effective, need low maintenance, and stable over a wide temperature range. Based on processing under changing temperature, polymers are categorized as thermosets and thermoplastics as listed in the Fig 1, also thermoplastics including elastomers can be divided into semicrystalline and amorphous polymers. Both the thermoset and thermoplastic.




Fig 1: Polymers are classified as thermosets and thermoplastics under changing temperature

An amorphous thermoplastic material has no specific molecular structure and is normally a solid, clear, stiff material with low shrinkage, for example, polystyrene. In comparison, a crystalline polymer has a systematized, “crystal-like” structure, but also comprises amorphous material. It is usually known as a semi-crystalline thermoplastic material. These types of plastics are commonly tougher and less fragile compared to amorphous thermoplastics. It is also common for them to have a higher heat distortion temperature. Additionally, these plastics are translucent, or opaque, and have a high shrinkage. Several categories of materials have been used as radiation shielding barriers to keep a safe environment for everyday practice in all radiation conveniences. Several features can classify the proper shielding material to be used, including a high atomic number for gamma radiation shielding such as (Ba), (Pb), and (Bi). Whereas elements of low atomic numbers are preferably used for neutron attenuation^[4]. However, many constraints burden the use of such modern shielding materials such as the cost, heaviness, and toxicity. To improve the polymer’s performance and characteristics, a stiff material called filler can be added to the polymer matrix to form a polymer composite. The combination between the filler and the polymer matrix provokes the formation of a mixture that influences the polymer–composite properties by retaining the properties of both the filler and the polymer. The composite materials are named according to the reinforcement and the matrix material constituting them. There are many types of matrix materials such as metal matrix composites, polymer matrix composites, ceramic matrix composites, and epoxy resin matrix composites. The availability of radiation shielding materials that can be molded into specific shapes and used even at high temperatures is quite significant for medical and industrial procedures^[6].

The resistance of a material to radiation is attributed to many factors such as the type of radiation used, the rate of absorbed dose, radiation exposure (pulsed or continuous), area and size of the material, and the surrounding environment (pressure, temperature, electric, or magnetic field). But in inorganic materials, the radiation resistance depends on the type of chemical bond and crystal structure of the material. Due to their relatively high processing ability and durability, polymer composite materials are vastly used in various fields of industry. In 1916, the first polymer composite was used as a phenol–formaldehyde resin (wood flour) by bakelite. Recently, about 10,000 fillers are known and used. The main duty of the filler is to provide

the material with special properties and cost-effectiveness^[14]. Composites of polymer materials are superior due to their merits in flexibility, low cost, workability, mechanical stability, and high aspect ratio. Also, the research studies confirmed that composite materials not only are better in radiation resistance but also have thermal stability and high mechanical properties. Numerous studies have reported the use of polymer composites as gamma-radiation shields^[12].

References

1. Laith Ahmed Najam, Abdalsattar Kareem Hashim, Abdalsattar Kareem Hashim, Ammar Salah Hameed. Estimation of Radon Exhalation Rate, Radium Activity and Uranium Concentration in Biscuit Samples in Iraq. *Iranian Journal of Medical Physics*. 2019; 16(2):152-157.
2. Salman EF, Muttelab MK, Manii JK. Radioactivity Natural Environmental Radiation in Middle of Iraq Governorates. *Annals of Agri-Bio Research*. 2019; 8(2):1-4.
3. Wood J. *Computational Methods in Reactor Shielding*, Pergamon Press, Oxford, 1982.
4. Akkurt İ, Akyıldırım H, Mavi B, Kılınçarslan S, Başığit C. Gamma-ray shielding properties of concrete including barite at different energies. *Progress in Nuclear Energy*. 2010; 52(620):620-623.
5. Akkurt İ, El-Khayatt AM. Radiation shielding properties of concrete containing magnetite. *Progress in Nuclear Energy*. 2021; 137(103776).
6. Shivalinge Gowda, Krishnaveni S, Yashoda T, Umesh TK, Ramakrishna Gowda. Photon mass attenuation coefficients, effective a numbers and electron densities of some thermoluminescent dosimetric mpounds. *Pramana: Journal of Physics*. 2004; 63(3):529-541.
7. Han I, Demir L, Şahin M. Determination of mass attenuation coefficients, effective atomic and electron numbers for some natural minerals. *Radiation Physics and Chemistry*. 2009; 78(9):760-764.
8. Hasan Wasan K, Mahdi Jassim T, Hameed Ammar S. Effect of CuO Nanoparticles on Linear and Nonlinear Optical Properties of Polymer/MgO Nanocomposites. *Quantum Optics*. 2019; 50(4):279-291.
9. Kılınçarslan Ş, Başığit C, Akkurt İ, Gazi. Studies on mass energy-absorption coefficients and effective atomic energy-absorption cross sections carbohydrates. *Radiation Physics and Chemistry*. 2015; 109:89-94.
10. Laxman C, Dayanand R. Attenuation Coefficient of Soil Samples by Gamma ray Energy. *Research Journal of Recent Sciences*. 2012; 1(9):41-48.
11. Madbouly AM, Atta ER. Comparative Study between Oxide and Lead Nitrate Polymer as Gamma-Radiation Shielding Material. *Journal of Environmental Protection*. 2016; 7(2):268-276.
12. Laith Ahmed Najam, Abdalsattar Kareem Hashim, Hussein Abdulkareem Ahmed, Israa M Hassan. Study the Attenuation Coefficient of Granite to Use It as Shields against Gamma Ray. *Scientific Research Publishing*. 2016; 4(2):33-39.
13. Oleksy M, Heneczowski M, Galina H. Chemosetting resins containing fillers. I. Unsaturated polyester resin compositions containing modified smectites. *Journal of Applied Polymer Science*. 2005; 96(3):793-801.
14. Wasan KH, Naseer Almkhtar. The 7th international conference Applied Science and Technology 27-28

- March, 2019, College of Science, University of Kerbala, 2019.
15. Ravikumar P, Somashekar RK. Determination of the radiation dose due to radon ingestion and inhalation. *International Journal of Environmental Science and Technology*. 2014; 11(2):493-508.
 16. Akkurt İ, Günöglu K, Başığit C, Akkaş A. Determination of Radiation Attenuation Coefficients in Concretes Containing Different Wastes. *Acta Physical Polonica Series a*. 2016; 130(1):316-317.
 17. Almayahi BA, Entisar Farhan S. Investigation of the Atomic Properties for Helium-Like. *Open Science Journal of Modern Physics*. 2015; 2(5):80-82.