



إنشاء نموذج لتخمين نسبة الجبس المثلى للسمنت البورتلاندي

رسالة

مقدمة إلى كلية الهندسة في جامعة بابل

كجزء من متطلبات إكمال الماجستير في علوم

الهندسة المدنية

من قبل

زينب حسن عبد العباس

إشراف

أ.م.د. مهدي صالح عيسى

أ.م.د. غالب محسن حبيب

Ministry of High
Education and
Scientific Research



University of Babylon
of Engineering
Civil Department

CONSTRUCTING A MODEL FOR PREDICTING OPTIMUM GYPSUM CONTENT OF PORTLAND CEMENT

A THESIS

Submitted to The College of Engineering
of The University of Babylon in Partial
Fulfillment of The Requirements
for The Degree of Master
of Science in Civil
Engineering

By

ZAINAB HASSAN ABDUL-ABASS

B.Sc. ٢٠٠٤ Supervised by

Asst. Prof. Dr. MAHDI S. ESSA

Asst. Prof. Dr. GHALIB M. HABEEB

بِسْمِ اللَّهِ الرَّحْمَنِ الرَّحِيمِ

وَيَسْأَلُونَكَ عَنِ الرُّوحِ قُلِ الرُّوحُ مِنْ أَمْرِ رَبِّي وَمَا أُوتِيتُمْ مِنَ الْعِلْمِ إِلَّا قَلِيلًا

وَيَسْأَلُونَكَ عَنِ الرُّوحِ قُلِ الرُّوحُ مِنْ أَمْرِ رَبِّي وَمَا أُوتِيتُمْ مِنَ الْعِلْمِ إِلَّا قَلِيلًا

صَدَقَ اللَّهُ الْعَظِيمُ

الخلاصة

تم اشتقاق نموذج رياضي لتخمين نسبة الجبس المثلى للسمنت البورتلاندي في أعمار ٣، ٧، ٢٨، و ٦٠ يوم، الذي يمنح السمنت مقاومة انضغاط قصوى. للحصول على هذا النموذج الدراسة الحالية قسمت إلى جزئين:

١. تطوير نموذج إحصائي لتخمين مقاومة الانضغاط للسمنت البورتلاندي. وذلك لان هذا النموذج هو الأساس لتطوير نموذج نسبة الجبس المثلى للسمنت. إن نموذج تخمين مقاومة الانضغاط بني باستخدام تحليل الانحدار و مستند على (٤٠) من عينات السمنت المختلفة مأخوذة من (٧) معامل سمنت عراقية مختلفة، سمنت هندي، و سمنت كويتي. (٢٦) من العينات كانت سمنت بورتلاندي اعتيادي بينما الـ (١٤) عينة الأخرى كانت سمنت بورتلاندي مقاوم للكبريتات.

لتحسين دقة تخمين مقاومة الانضغاط، تم توجيه الاهتمام نحو الاختيار الصحيح للمتغيرات المستخدمة في هذا النموذج. عدد المتغيرات غير المعتمدة المدروسة كان (١٦). هذه المتغيرات هي (C_٢S, C_٣S, C_٣A, C_٤AF)، النعومة (مقاسة بطريقة Blaine)، الأكاسيد الثانوية MgO، الجير الحر free CaO، SO_٣، والمتغيرات التي يحصل عليها من التحليل الكيميائي للسمنت مثل معامل السليكا (SM)، نسبة الألومينا (AR)، الفقدان أثناء الإيقاد (LOI)، المخلفات غير الذائبة (IR)، ومعامل الإشباع الجيري (LSF). بالإضافة إلى زمن التصلب الابتدائي و النهائي و فحص الثبات (معبراً عنه بطريقة المحمم المائي)

محاولات جادة تمت لإدخال المتغيرات في مجاميع مختلفة لاختبار المتغيرات التي لها تأثير أكثر تميز على مقاومة الانضغاط، حتى إنجاز الشكل النهائي للنموذج المقترح.

تم اختبار صلاحية النموذج المقترح لتخمين مقاومة الانضغاط في أعمار مختلفة وذلك بفحص خمس عينات من السمنت بأعمار ٢، ٣، ٧، ١٤، ٢١، ٢٨، و ٦٠ يوم. كذلك تم عمل مقارنة للنموذج باستخدام بيانات أخرى (غير المستحصلة في الدراسة الحالية). لقد وجد إن النموذج المقترح يعطي نتائج جيدة وهذا يشير إلى الاختيار الصحيح لشكل النموذج و المتغيرات المستخدمة في النموذج.

معامل الارتباط للصيغة النهائية لنموذج تخمين مقاومة الانضغاط (عندما يتضمن النموذج جميع المتغيرات مع اعتبار زمن الفحص متغير غير معتمد اساسي) كان (٠.٩٩٦٦)، قيمة الخطأ القياسي كانت (٠.٢٠١٤)، و الاختلاف بين المقاومة الحقيقية و المخمّنة كانت (±٠.٢ MPa).

٢. صياغة مشكلة تحقيق الأمثلية، وصياغة الشكل النهائي للنموذج المقترح لتخمين نسبة الجبس المثلى للسمنت.

الشيء الأكثر أهمية في هذه الدراسة هو الحصول على استعمال مفهوم تطبيق اشتقاق رياضي على النماذج الإحصائية. تمت المحاولة لتطبيق طريقة تحقيق الأمثلية الكلاسيكية على نموذج تخمين مقاومة الانضغاط للحصول على قيمة $SO_3\%$ التي تزيد مقاومة الانضغاط. لقد وجد إن الاشتقاق الرياضي للنموذج الإحصائي لا يعطي نتائج جيدة عندما يكون النموذج الإحصائي دالة للزمن. لكنه يعطي نتائج جيدة عند استعمال نموذج خاص لكل عمر. انه من غير الممكن بناء نموذج لكل عمر لذا تم اختيار أربعة أعمار لبناء نموذج لكل منها لتخمين مقاومة الانضغاط وهذه الأعمار هي ٣، ٧، ٢٨، و ٦٠ يوم.

صلاحية مثل هذا الاشتقاق فحصت باستعمال بيانات تجريبية موثوقة أخذت من بحث آخر. لقد وجد إن نسبة الجبس المثلى المحسوبة من النموذج المقترح قريبة من القيم الفعلية.

كذلك وجد إن نعومة السمنت، C_3S ، C_2S ، C_3A ، C_4AF ، فحص الثبات، و زمن التصاب الابتدائي و النهائي هي العوامل الرئيسية في نموذج تخمين نسبة الجبس المثلى للسمنت.

ABSTRACT

A mathematical model is driven to predict the Optimum Gypsum Content (O.G.C.) of Portland cement at ages of ٣, ٧, ٢٨, and ٦٠ days, which imparts the cement maximum compressive strength. To obtain such model the present study is divided into two parts:

١. Development of statistical model for prediction of compressive strength of Portland cement. The reason is that such model is the basis to development of the O.G.C. model of cement.

The compressive strength prediction model was built by using regression analysis and based on (٤٠) different cement samples taken from (٧) different Iraqi cement factories, Indian cement, and Kuwaiti cement. (٢٦) of the samples were ordinary Portland cement while the other (١٤) samples were sulphate resisting Portland cement.

To improve the accuracy of the compressive strength prediction, attention has been drawn towards right selection of the variables which are used in this model. The number of the studied independent variables was (١٦). These variables are C_3S , C_2S , C_3A , C_4AF , fineness (in terms of Blaine specific surface),

the minor oxides MgO, free CaO, SO_r, and the variables obtained from the chemical analysis of cement like silica modulus (SM), alumina ratio (AR), loss on ignition (LOI), insoluble residue (IR), and lime saturation factor (LSF), in addition to initial and final setting time, and unsoundness (in terms of autoclave expansion).

Serious attempts were made to introduce the variables in various combinations to examine the variables which have the most significant effect on the compressive strength, until attaining the final form of the proposed model.

The validity of the proposed model to predict the compressive strength at various ages was checked by using five cement samples tested at ages of 1, 2, 3, 7, 14, 21, 28, and 60 days. A comparison of the present model using other data (other than those obtained in the present study) was made. It was found that the proposed model yields good results and refers to the right selection of the model form and of the variables used in the model.

The correlation coefficient of the final form of the compressive strength prediction model (i.e when all variables are included in the model and taking of time of testing (t) as the main independent variable) was (0.9966), the value the standard error was (0.2014), and the difference between the observed and the predicted strength was (± 2 MPa.).

2. Formulation of the optimization problem, and formulation of the final form of the proposed model for predicting O.G.C. of cement.

The most important thing in this study is to get use of the concept of applying mathematical derivation on statistical models. An attempt is made to apply Classical Optimization Method on the compressive strength prediction model to obtain the SO_r% value that maximize the compressive strength. It was found that the mathematical derivation of the statistical model does not yield good results when the statistical model is a function of time. But it yields good results when a special model is used for each age. It is impossible to produce a model for each age, hence, four ages were selected to build a model for each one of them to predict compressive strength. These ages are 3, 7, 28, and 60 days.

The validity of such derivation was examined by using reliable available experimental data from other research. It was found that the calculated O.G.C. from the proposed model is close to the actual value of the O.G.C.

The fineness of cement, C_{rS} , C_{vS} , C_{rA} , C_{zAF} , unsoundness, initial setting time, and final setting time are the major factors in O.G.C. prediction model.

LIST OF CONTENTS

SUBJECTS	PAGE
----------	------

Acknowledgement.....	I
Abstract.....	II
List of Contents.....	IV
List of Figures.....	VII
List of Tables.....	X
Notations.....	XII

CHAPTER ONE: INTRODUCTION

1.1 General	1
1.2 Modeling of The Compressive Strength of Cement.....	2
1.3 Optimization.....	4
1.4 Modeling of The Optimum Gypsum Content of Cement.....	4
1.5 The Objectives of The Present Work.....	5
1.6 The Thesis Layout.....	6

CHAPTER TWO: LITERATURE REVIEW

۲.۱ Chemical Composition of Portland Cement.....	۷
۲.۲ Sulfate Attack.....	۱۱
۲.۳ Effect of Gypsum on Some Properties of Cement.....	۱۳
۲.۳.۱ Effect of Gypsum on Setting Time.....	۱۴
۲.۳.۲ Effect of Gypsum on Compressive Strength.....	۱۵
۲.۳.۳ Effect of Gypsum on Expansion.....	۱۸
۲.۳.۴ Effect of Gypsum on Shrinkage.....	۱۹
۲.۳.۵ Effect of Gypsum on Heat Evolution.....	۲۰
۲.۴ Factors Affecting Optimum Gypsum Content.....	۲۱
۲.۴.۱ Chemical Composition of Cement.....	۲۱
۲.۴.۲ Fineness of Cement.....	۲۴
۲.۴.۳ Source of Gypsum.....	۲۵
۲.۴.۴ Glass Content.....	۲۶
۲.۴.۵ Curing time, Curing method, and Curing temperature.....	۲۷
۲.۴.۶ Type of Calcium Sulfate.....	۲۸
۲.۵ Statistical Models for The Optimum Gypsum Content in Cement..	۳۰

SUBJECTS

PAGE

۲.۵.۱ Haskell`s Model.....	۳۰
۲.۵.۲ Meissner`s Model.....	۳۱
۲.۵.۳ Ost` Model.....	۳۱
۲.۵.۴ Hobbs`s Models.....	۳۱
۲.۵.۵ Abdul-Latif`s Models.....	۳۲
۲.۶ Compressive Strength.....	۳۵
۲.۷ Statistical Models for Strength in Cement.....	۳۶

CHAPTER THREE: EXPERIMENTAL WORK

۳.۱	Introduction	۴۹
.....		۴۹
۳.۲ Materials.....		۴۹
۳.۲.۱ Cement.....		۵۰
۳.۲.۲ Sand.....		۵۰
۳.۲.۳		۵۶
Water.....	۳.۳	۵۶
Preparation of Mortar Cubes.....		۵۶
۳.۴ Curing.....		۵۷
۳.۵ Compressive Strength Test.....		۵۷

3.6 Setting Time	
Test.....	
3.7 Soundness Test.....	

CHAPTER FOUR: ANALYSIS OF RESULTS AND DISCUSSION

4.1 Development of statistical models for prediction of compressive strength of cement.....	58
4.1.1 Factors Affecting Strength of Cement.....	58
4.1.1.1 Individual Effect of Main Compounds.....	59
4.1.1.2 Effect of C_3S	60
4.1.1.3 Effect of C_2S	62
4.1.1.4 Effect of C_3A	63
4.1.1.5 Effect of C_4AF	64
4.1.1.6 Effect of MgO.....	66
4.1.1.7 Effect of Free CaO.....	67
4.1.1.8 Effect of SO_3	68
4.1.1.9 Effect of Loss on Ignition.....	

4.2.1.10 Effect of Insoluble Residue.....	PAGE
---	-------------

SUBJECTS

ξ.1.1.11 Effect of Lime Saturation Factor.....	79
ξ.1.1.12 Effect of Unsoundness.....	79
ξ.1.1.13 Effect of Silica Modulus and Alumina Ratio.....	71
ξ.1.1.14 Effect of Initial and Final Setting	73
Time.....	70
ξ.1.1.15 Effect of Fineness.....	
ξ.1.2 The Statistical Regression Models for Prediction of	76
Compressive Strength of Portland Cement.....	76
ξ.1.2.1 Models	83
Development.....	83
ξ.1.2.2 Residual Examination.....	86
ξ.1.2.3 Examination of Statistical	88
Models.....	
ξ.1.2.4 Comparison with Data from Other Sources	91
.....	91
ξ.2 Formulation of The Optimization Problem.....	98
ξ.3 The Statistical Regression Models for Prediction of Compressive	98
Strength of Portland Cement at ages of 3, 7, 28, and 60 Days.....	
ξ.3.1 Model Development.....	101
ξ.3.2 Residual Examination.....	
ξ.3.3 Examination of Statistical	104
Models.....	100
ξ.3.4 Application of The Classical Optimization Method on 3,	
7, 28, and 60 days compressive strength	
models.....	
ξ.3.5 Examination of The Mathematical Derivation and	
Comparison with Other Models.....	
ξ.4 The Discussion of The Factor Affecting O.G.C. of Cement.....	

CHAPTER FIVE: CONCLUSIONS AND RECOMMENDATIONS

ο.1	109
Conclusions.....	110
ο.2 Recommendation for Future Studies.....	
	111
References.....	
Appendix.....	

LIST OF FIGURES

<i>TITLE</i>	<i>PAGE</i>
Figure (2-1): The Development of Compressive Strength with Different Amounts of SO _r (Haecker et al. 2000).....	18
Figure (2-2-a): Degree of Hydration of C _r A with Different Amounts of SO _r (Haecker et al. 2000).....	21
Figure (2-2-b): The Rate of Ettringite Formation with Different Amounts of SO _r (Haecker et al. 2000).....	22
Figure (2-3): Relative Strength Development of Portland Cement mortar cubes as a Percentage of – 28 Day Strength. Mean Values Adopted from Gebhardt 1990.....	37
Figure (4-1): Relationship between C _r S and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement...	60
Figure (4-2): Relationship between C _r S and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement...	61
Figure (4-3): Relationship between C _r A and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement...	63
Figure (4-4): Relationship between C ₃ AF and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement...	64
Figure (4-5): Relationship between MgO and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement...	65
Figure (4-6): Relationship between Free CaO(%) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	66
Figure (4-7): Relationship between SO _r and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	67

Days Compressive Strength of Portland Cement....	
Figure (4-8): Relationship between Loss on Ignition (%) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	78
Figure (4-9): Relationship between Insoluble Residue(%) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	79

<i>TITLE</i>	<i>PAGE</i>
---------------------	--------------------

Figure (4-10): Relationship between LSF and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement..	70
Figure (4-11): Relationship between Unsoundness(%) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	70
Figure (4-12): Relationship between Alumina Ratio and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	72
Figure (4-13): Relationship between Silica Modulus and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	73
Figure (4-14): Relationship between Initial Setting Time (minute) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	74
Figure (4-15): Relationship between Final Setting Time (minute) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	74
Figure (4-16): Relationship between Specific Surface Area of Cement (m^2/kg) and 3, 7, 28, and 60 Days Compressive Strength of Portland Cement.....	76
Figure (4-17): The Residuals Distribution of Compressive Strength Obtained by The Proposed Model for Ages of 3, 7, 28, and 60 Days.....	89
Figure (4-18): Graphical Representation of a Function $f(x)$ (Bunday ¹⁹⁸⁰ p.4).....	98
Figure (4-19): Residual Distributions for (a) 3 Days, (b) 7 Days, (c) 28 Days, and (d) 60 Days Compressive Strength for model 1*.....	99

Figure (4-20): Residual Distributions for (a) 3 Days, (b) 4 Days, (c) 5 Days, and (d) 6 Days Compressive Strength for Model α^*	99
Figure (4-21): Residual Distributions for (a) 3 Days, (b) 4 Days, (c) 5 Days, and (d) 6 Days Compressive Strength for Model α^*	

<i>TITLE</i>	<i>PAGE</i>
---------------------	--------------------

Figure (4-22): Residual Distributions for (a) 3 Days, (b) 4 Days, (c) 5 Days, and (d) 6 Days Compressive Strength for Model α^*	100
Figure (4-23): Residual Distributions for (a) 3 Days, (b) 4 Days, (c) 5 Days, and (d) 6 Days Compressive Strength for Model α^*	100

LIST OF TABLES

<i>TITLE</i>	<i>PAGE</i>
Table (٢-١): Step-wise Model presented by Abdul-Latif in ٢٠٠١	٢٤
Table (٢-٢): Physical and Chemical Requirements for Ordinary Portland Cement According to the Iraqi Standard IQS No.٥:١٩٨٤	٢٦
Table (٣-١): Cement Factories and The Type of Their Production with The Number of Sampls.....	٥٠
Table (٣-٢): Chemical Analysis for The Cements Used Throughout The Present Study.....	٥١
Table (٣-٣): Physical Properties for The Cements Used Throughout The Present Study.....	٥٣
Table (٣-٤): The Four Main Compounds for The Data Used Throughout The Present Study.....	٥٥
Table (٤-١): Regression Coefficients for The Compressive Strength Prediction Models.....	٨١
Table (٤-٢): Properties of Cement Used for Checking The Proposed Model.....	٨٥
Table (٤-٣): Observed and Predicted compressive Strength at Ages of ١, ٢, ٣, ٧, ١٤, ٢١, ٢٨, and ٦٠ Days Using The Fifth Model.....	٨٥
Table (٤-٤): Correlation Coefficients Using The Data of The Present Study with Data from Other Sources.....	٨٧
Table (٤-٥): Regression Coefficients for The ٣ Days Compressive Strength Prediction Model.....	٩٣
Table (٤-٦): Regression Coefficients for The ٧ Days Compressive Strength Prediction Model.....	٩٤
Table (٤-٧): Regression Coefficients for The ٢٨ Days Compressive Strength Prediction Model.....	٩٦
Table (٤-٨): Regression Coefficients for The ٦٠ Days Compressive Strength Prediction	١٠١
	١٠٣

Model.....
Table (4-9): Observed and Predicted Compressive Strength at Age of 3, 7, 28, and 90 Days Using The Fifth Model..... 104

Table (4-10): Values of Calculated Optimum SO_2 105

<i>TITLE</i>	<i>PAGE</i>
--------------	-------------

Table (4-11): Experimental and Calculated Optimum SO_2 for Data Obtained by Abdul-Latif (2001).....

NOTATIONS

Most of common symbols are listed below; others are defined where they appear in the research.

Symbol	Description
O.G.C.	Optimum Gypsum Content.
O.P.C.	Ordinary Portland Cement.
S.R.P.C.	Sulphate Resisting Portland Cement.
EEF	Early Ettringite Formation
DEF	Delayed Ettringite Formation
$f_{(t)}$	Compressive Strength at Time (t).
S_s	Specific Surface Area of Cement.
LOI	Loss on Ignition.
IR	Insoluble Residue.
LSF	Lime Saturation Factor.
SM	Silica Modulus.
AR	Alumina Ratio.
IST	Initial Setting Time.
FST	Final Setting Time.
R	Correlation Coefficient.
S.E.	Standard Error.
df	Difference between the actual and predicted strength
C.E.B.	Consultant Engineering Bureau

ACKNOWLEDGEMENT

First, thanks to **ALLAH HIS MAJESTY** for enabling me to complete this work.

It is a pleasure to express my deep appreciation to my supervisors Asst. Prof. Dr. Mahdi S. Essa and Asst. Prof. Dr. Ghalib M. Habeeb for their valuable guidance and support during the various stages of this project.

I would like to record my thanks to the staff of cement testing laboratory and to the staff of Consultant Engineering Bureau of University of Babylon.

I would also record my thanks to the staff of Al-Najaf Construction Laboratory.

Great thanks to the staff of civil engineering department especially, the chief of civil department Dr. Ammar Y. Ali for his assistance during the period of study at the University of Babylon.

Special thanks are presented to Huda Zuheir, Mr. Hussain Mared, and Zahra Abed for their assistance.

I am really grateful to my family for their encouragement and support during the course of this work.

Finally, thanks to all my friends for their forceful encouragement during the progress of this work especially, Dr. Aula Saad, Abeer Ibrahim, Abeer Saeed, Rand Sami, Saba Basim, Shireen Qasim, Nadia Moneim, and Nourass Nomass.

Zainab Hassan

٢٠٠٧

CERTIFICATION

We certify that this thesis titled "**Constructing a Model for Predicting Optimum Gypsum Content of Portland Cement**" was prepared by "**Zainab Hassan Abdul-Abass**" under our supervision at University of Babylon in partial fulfillment of the requirements for the degree of Master of Science in Civil Engineering.

Signature

Name :

Asst. Prof. Dr. Mahdi S. Essa
(Supervisor)

Date : / / ٢٠٠٧

Signature

Name :

Asst. Prof. Dr. Ghalib M. Habeeb
(Supervisor)

Date : / / ٢٠٠٧

CERTIFICATION

We certify that we have read this thesis, titled "**Constructing a Model for Predicting Optimum Gypsum Content of Portland Cement**", and as an examining committee examined the student "**Zainab Hassan Abdul-Abass**" in its contents and in what is connected with it, and that in our opinion it meet the standard of thesis for the degree of Master of Science in Civil Engineering.

Signature

Name :

Asst. Prof. Mr. Samir A. Al-Mashhadi
(Chairman)

Date : / / ٢٠٠٧

Signature

Name :

Asst. Prof. Dr. Haider T. Al-Damerchi
(Member)

Date : / / ٢٠٠٧

Signature

Name :

Asst. Prof. Mr. Ali A. Alwash
(Member)

Date : / / ٢٠٠٧

Signature

Name :

Asst. Prof. Dr. Mahdi S. Essa
(Supervisor)

Date : / / ٢٠٠٧

Signature

Name :

Asst. Prof. Dr. Ghalib M. Habeeb
(Supervisor)

Date : / / ٢٠٠٧

Approval of the Civil Engineering Department.
Head of the Civil Engineering Department.

Signature

Name : Asst. Prof. Dr. Ammar Y. Ali

Date : / / ٢٠٠٧

Approval of the Deanery of the College of Engineering.
Dean of the College of Engineering.

Signature

Name : Prof. Dr. Abdul-Wahed K. Rageh
University of Babylon

Date : / / ٢٠٠٧

Table (A- 1) Properties of Ordinary Portland Cements form Data Obtained by Consultant Engineering Bureau in University of Babylon (for The Period between ٢٠٠٠- ٢٠٠٣)

C _r S%	C _s S%	C _r A%	C _i AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	AR	SM	IST (min)	FST (min)	f _r (MPa)
3.43	30.21	9.18	11.2	4.07	2.18	0.78	320	2.92	0.70	0.87	1.79	2.38	90	240	23.0
3.42	38.20	11.33	9.73	4.1	2.28	0.70	300	2.97	0.01	0.87	1.97	2.18	120	220	20.0
4.00	34.31	7.97	11.19	4.4	2.11	0.90	320	2.74	0.42	0.87	1.40	2.33	120	240	23
4.90	43.1	10.07	9.98	2.93	2.7	1.29	342	2.43	0.74	0.84	1.80	2.3	80	100	17
7.97	29.77	10.09	9.49	4.27	2.32	0.78	320	3.40	0.37	0.89	1.87	0.24	120	220	22.3
7.27	39.23	12.21	9.49	3.93	2.74	0.89	320	2.07	0.47	0.80	2.11	2.14	90	190	23.8
1.78	27.73	8.40	9.87	4.72	2.0	0.78	320	2.39	0.23	0.89	1.72	2.43	80	200	21
4.72	44.27	9.29	9.98	2.78	2.70	0.89	400	3.39	0.07	0.83	1.7	2.47	00	170	20
7.27	31.18	10.47	9.0	4.4	2.34	0.71	374	3.38	0.00	0.88	1.9	2.20	120	240	23
4.73	34.14	10.12	9.20	4.07	2.24	0.77	339	2.7	0.8	0.87	1.89	2.38	110	230	27.3
2.04	27.72	8.30	9.87	3.97	2.19	0.78	307	3.87	0.47	0.9	1.71	2.42	100	270	20
7.27	41.3	12.44	9.73	2.7	2.78	1.12	320	1.12	0.97	0.80	2.1	2.14	90	200	17
7.13	41.74	11.02	9.20	4.80	2.40	0.78	338	1.89	0.72	0.84	2	2.34	130	190	19.2
7.07	32.48	9.29	9.98	2.73	2.71	1.78	301	1.8	0.01	0.89	1.7	2.37	130	200	18.3
0.78	39.74	9.70	9.20	3.9	2.20	0.78	320	1.83	0.37	0.80	1.80	2.30	80	270	18.1
0.87	38.07	9.30	9.0	4.70	2.03	0.77	334	2.28	0.30	0.80	1.77	2.0	140	200	21
3.17	28.27	7.07	10.83	3.78	2.20	0.71	320	1.77	0.41	0.89	1.38	2.0	100	180	20
8.87	30.37	8.48	10.1	4.37	2.44	0.77	280	2.27	0.0	0.88	1.7	2.41	100	240	19
2.40	27.03	8.24	9.87	2.24	2.33	0.77	320	2.21	0.00	0.89	1.7	2.74	110	180	19.7
7.70	31.1	9.97	10.1	3.70	2.27	0.84	310	2.13	0.0	0.88	1.77	2.27	120	190	22
3.71	30.37	11.21	9.87	3.17	2.38	0.72	320	1.43	0.42	0.87	1.94	2.22	110	170	20.8
4.49	33.04	11.18	9.20	4.73	2.20	0.07	334	2.30	0.24	0.87	2.02	2.24	100	180	21.0
7.87	31.81	10.30	9.49	3.84	2.28	0.77	338	1.20	0.7	0.88	1.89	2.33	100	170	21
8.83	33.2	0.48	12.03	3.77	2.1	0.72	310	1.28	0.71	0.87	1.14	2.47	110	170	20.7

Continue Table (A- 1)

N o.	C _r S %	C _s %	C _r A %	C _i A F%	Mg O%	SO _r %	Fre e Ca O%	S _s (Blai ne) (m ² / kg)	L.O. l%	IR %	L.S. F%	AR	S M	IST (mi n)	FS T (mi n)	f _r (M Pa)	f _v (M Pa)
20	34.87	33.4	10.39	9.71	4.21	2.20	0.78	334	2.17	0.40	0.88	1.88	2.8	90	100	20	28
26	41.2	27.79	9.8	10.09	3.11	2.00	0.78	374	2.70	0.43	0.9	1.7	2.18	110	170	24.1	33.3
27	37.18	32.0	10.20	9.87	3.97	2.31	0.7	300	1.70	0.31	0.8	1.8	2.27	100	170	19.7	27.7
28	39.74	30.72	7.8	10.09	3.70	2.28	0.78	347	1.93	0.20	0.8	1.49	2.43	90	100	23.0	28.3
29	38.17	29.74	11.48	9.3	4.00	2.4	0.78	310	1.71	0.42	0.8	2.0	2.17	100	180	20.3	28.9
30	27.42	38.37	13.27	9.4	4.4	2.31	0.7	310	1.91	0.07	0.8	2.0	2.03	90	170	19.7	27.7
31	37.87	31.81	10.30	9.4	3.84	2.28	0.7	338	1.20	0.7	0.8	1.89	2.33	100	170	21	29
32	38.74	30.02	9.3	9.7	4.1	2.3	0.78	270	2.11	0.32	0.8	1.73	2.8	110	200	19.0	27.0
33	37.0	33.0	7.2	11.0	3.7	2.2	0.8	343	2.2	0.0	0.8	1.0	2.0	80	100	19.0	28.0

۳	۸۱	۲۴	۸	۲	۱	۳	۴		۷	۲۳	۷	۳۸	۴۲		۰	۸	۰
۳	۳۰.	۳۲.	۹.۷	۹.۸	۴.۰	۲.۳	۰.۷	۳۲۰	۲.۳	۰.	۰.۸	۱.	۲.	۹۰	۱۸	۱۹	۲۷.
۴	۸۴	۱۳	۷	۷	۰	۰	۸		۰	۲۹	۸	۷۷	۳		۰		۸
۳	۲۸.	۴۰.	۹.۸	۸.۸	۳.۸	۲	۱.۰	۳۲۰	۲.۸	۰.	۰.۸	۱.	۲.	۱۴	۲۴	۲۱.	۲۷.
۰	۸۹	۴۷	۴	۸	۰	۲	۷		۱	۷۱	۰	۹۱	۰۰			۸	۰
۳	۲۷.	۳۹	۱۴.	۹.۷	۳.۲	۲.۴	۰.۸	۳۰۱	۱.۷	۰.	۰.۸	۲.	۱.	۱۰	۱۹	۲۱.	۲۸
۶	۰۰	۳۹	۰۸	۱	۷	۲	۹		۲	۴۳	۷	۳۸	۹۱		۰	۷	
۳	۳۷.	۳۲.	۹.۸	۹.۴	۴.۲	۲.۳	۰.۷	۳۰.۸	۲.۱	۰.	۰.۸	۱.	۲.	۱۱	۱۹	۲۳.	۲۹.
۷	۰.۲	۹۱	۲	۹	۰	۱	۸		۴	۰۱	۷	۸۲	۳۷			۸	۹
۳	۳۸.	۳۰.	۸.۷	۱۱.	۳.۷	۲.۳	۰.۷	۳۱۰	۲.۱	۰.	۰.۸	۱.	۲.	۸۰	۱۷	۲۲.	۲۹
۸	۴۳	۲۹	۸	۰.۷	۷	۰	۸		۱	۰	۸	۰۰	۲۳		۰	۱	
۳	۳۷.	۳۲.	۷.۷	۱۱.	۳.۸	۲.۳	۰.۷	۳۳۰	۳.۰	۰.	۰.۸	۱.	۲.	۱۱	۲۱	۲۲.	۳۰.
۹	۷۷	۷۴		۲	۰	۱	۸		۳	۷۳	۷	۲۲	۷۱			۴	۳
۴	۳۱.	۳۷.	۹.۰	۹.۹	۴.۳	۲.۰	۰.۸	۳۲۹.	۲.۷	۰.	۰.۸	۱.	۲.	۹.	۱۷	۱۹.	۲۷.
۰	۴۹	۷۳	۷	۸	۰	۳	۴		۷	۴	۰	۷۸	۳۹			۷	۹
۴	۳۰.	۳۳.	۱۰.	۹.۸	۳.۴	۲.۳	۰.۷	۳۱۰.	۲.۲	۰.	۰.۸	۱.	۲.	۱۰	۱۷	۲۱.	۲۸.
۱	۰.۷	۷۰	۱۰	۷	۳	۰	۲		۳	۰۰	۷	۸۲	۳			۷	۳
۴	۳۸.	۳۱.	۷.۲	۱۱.	۴.۲	۲.۱	۰.۷	۳۳۸.	۱.۷	۰.	۰.۸	۱.	۲.	۱۰	۱۷	۲۰.	۲۸
۲	۰۰	۸۷	۰	۰.۷	۹	۳	۸		۸	۰۱	۷	۳۹	۴۴			۳	
۴	۰۱.	۲۰.	۹.۷	۰.۸	۲.۸	۲.۰	۰.۹	۳۰۰	۱.۰	۰.	۰.۹	۱.	۲.	۱۱	۲۲	۲۰.	۲۸
۳	۴	۴۰	۴	۸	۹	۰	۰		۱	۳۱	۳	۸۹	۴۴			۰	
۴	۴۲.	۲۷.	۷.۷	۱۰.	۳.۹	۲.۲	۰.۷	۲۸۰	۲.۷	۰.	۰.۸	۱.	۲.	۱۰	۲۱	۲۱.	۲۸.
۴	۳۷	۷۲	۰	۳۴	۰	۰	۸		۷	۴	۹	۴۹	۴۰			۳	۷
۴	۴۱.	۳۰.	۸.۳	۸.۷	۳.۷	۲.۲	۰.۷	۳۰۱	۲.۸	۰.	۰.۸	۱.	۲.	۱۱	۲۲	۲۲.	۳۱
۰	۱۷	۱۹	۷	۷	۰	۷	۲		۰	۳۳	۸	۷۳	۷۱			۹	
۴	۳۷.	۳۴.	۷.۳	۱۱.	۳.۴	۲.۳	۰.۷	۲۹۰	۲.۳	۰.	۰.۸	۱.	۲.	۱۲	۲۴	۲۲	۳۰.
۶	۰.۱	۰.۷	۸	۸	۰	۱	۸		۳	۴	۴	۲۹	۰۲				۰
۴	۴۸.	۲۴.	۷.۰	۸.۷	۲.۷	۱.۹	۱.۰	۲۸۰.	۳.۰	۰.	۰.۹	۱.	۲.	۱۲	۲۴	۱۸.	۲۷
۷	۲۸	۱۸	۲	۷	۱	۰	۷		۱	۷۲	۱	۷۳	۷۹			۰	
۴	۴۳.	۲۷.	۷.۴	۹.۸	۴.۱	۲.۳	۰.۸	۲۷۹.	۳.۷	۰.	۰.۸	۱.	۲.	۱۳	۲۰	۲۳	۳۰.
۸	۱۸	۰.۷	۹	۷	۴.۱	۲	۴		۷	۴۰	۹	۳۹	۷۸				

Continue Table (A- 1)

C _r S%	C _r S%	C _r A%	C _r AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ^۲ /kg)	L.O.I.%	IR%	L.S.F.%	AR	SM	IST (min)	FST (min)	f _r (MPa)
۹.۱۰	۳۰.۹۶	۷.۷۴	۹.۷۱	۳.۹۰	۲.۲۰	۰.۷۸	۲۹۰.۰	۳.۴۲	۰.۷۱	۰.۸۸	۱.۰۰	۲.۷۱	۱۲.۰	۲۴.۰	۲۲.۳۱
۷.۷۶	۳۲.۷۴	۷.۷	۱۱.۲	۳.۸۰	۲.۳۱	۰.۰۱	۳۳۰	۳.۰۳	۰.۷۳	۰.۸۷	۱.۲۲	۲.۷۱	۱۱.۰	۲۱.۰	۲۲.۴
۷.۲۶	۳۱.۳۹	۱۱.۳۰	۹.۱۲	۴.۱۱	۲.۳۲	۰.۷۲	۳۱۹.۹	۲	۰.۷۰	۰.۸۸	۲.۰۷	۲.۲۰	۱۰.۰	۱۹.۰	۲۲.۳
۰.۷۴	۳۰.۱۳	۷.۷۱	۱۲.۱۱	۳.۷۰	۲.۳۹	۰.۸	۳۰۹.۱	۱.۷۰	۰.۷۱	۰.۸۷	۱.۲۶	۲.۳۰	۱۲.۰	۲۳.۰	۲۲.۲
۳.۸۲	۳۰.۰۸	۷.۷۴	۱۲.۱۷	۴.۱۹	۲.۲۱	۰.۴۰	۳۲۳.۴	۱.۸۳	۱.۳	۰.۸۷	۱.۲۷	۲.۳	۱۱.۰	۱۸.۰	۲۰.
۷.۳۶	۴۱.۴	۹.۸۶	۹.۴۳	۳.۸۱	۲.۷۰	۰.۰۴	۳۷۰.۰	۱.۹۶	۰.۷۹	۰.۸۳	۱.۸۳	۲.۴۰	۸.۰	۱۸.۰	۱۹
۷.۳۸	۳۹.۲۳	۱۳.۰۲	۸.۰۲	۴.۱۳	۲.۰۲	۰.۷۶	۲۷۳.۹	۱.۸۴	۰.۰۲	۰.۸۰	۲.۳۹	۲.۱۸	۷.۰	۱۸.۰	۱۷
۴.۴۷	۲۸.۱	۴.۴	۱۳.۱	۳.۴۱	۲.۲۸	۰.۸۶	۳۲۴.۴	۱.۰۶	۰.۷۸	۰.۸۹	۱.۰۲	۲.۴۷	۱۰.۰	۲۴.۰	۲۲.۸
۰.۶۹	۳۲.۸۲	۱۱.۱۹	۹.۶۲	۴.۲۸	۲.۰	۰.۸۲	۳۱۲.۲	۰.۹۸	۰.۷۱	۰.۸۸	۱.۹۸	۲.۲۲	۱۶.۰	۲۴.۰	۲۱.۳
۸.۴۸	۳۰.۹۰	۱۰.۱۷	۹.۷۴	۴.۲۰	۲.۳۲	۰.۷۷	۳۲.۰۴	۱.۱۷	۰.۰۰	۰.۸۹	۱.۸۴	۲.۳	۱۴.۰	۲۱.۰	۲۰.۴
۰.۶۹	۲۸.۰۹	۹.۹۶	۹.۷۴	۴.۲۸	۲.۶۶	۰.۷۱	۳۱۲.۲	۱.۲۸	۰.۷۱	۰.۹	۱.۸۱	۲.۳	۱۰.۰	۲۱.۰	۲۱.۹
۷.۸۴	۳۴.۰۰	۷.۲۱	۹.۶۱	۳.۲	۲.۷۱	۰.۰۶	۳۴۱.۶	۲.۰	۱.۳	۰.۸۶	۱.۳۸	۲.۹۳	۶.۰	۱۶.۰	۲۰.
۸.۸۱	۴۱.۰۶	۰.۷۲	۱۳.۰۷	۲.۹	۲.۴۳	۱.۰۱	۲۹۹.۸	۳.۱	۰.۷۰	۰.۸۳	۱.۱۴	۲.۳۸	۷.۰	۱۶.۰	۲۰.۶
۰.۱۴	۴۸.۱۰	۸.۹۶	۱۰.۱	۲.۴	۲.۸	۱.۶۱	۲۷۱.۴	۳.۶	۱.۳۸	۰.۸۱	۱.۶۶	۲.۰۱	۱۱.۰	۱۸.۰	۱۹.۷
۱.۹۰	۴۹.۲۶	۷.۷	۹.۹۸	۳.۳	۲.۷	۰.۶۰	۳۹۰.۳	۲.۳۲	۰.۸۶	۰.۷۹	۱.۴۱	۲.۹۱	۸.۰	۱۶.۰	۱۸

37.3	31.72	9.04	1.22	3.70	2.73	1.31	333.83	1.87	0.97	0.87	1.70	2.43	9.0	170	17.8
37.19	43.2	0.7	12.78	3.8	2.3	0.92	303.7	2.31	1.3	0.81	1.14	0.44	70	17.0	19
39.71	37.91	9.74	1.09	3.17	2.88	0.8	343.8	2.0	1.39	0.84	1.78	2.20	8.0	17.0	19.7
30.26	37.78	7.97	11.26	3.82	2.7	0.39	343.8	2.4	1.42	0.84	1.40	2.33	9.0	19.0	17
34.8	32.29	11.79	9.87	4.2	2.7	0.33	333.9	1.97	0.79	0.87	2.01	2.09	14.0	24.0	2.0
30.14	32.03	1.07	1.34	4.38	2.08	0.07	310.3	2.19	0.78	0.87	1.81	2.14	12.0	24.0	22.2
39.12	29.09	12.94	9.98	2.71	2.2	0.84	333.9	1.0	0.32	0.9	2.12	1.99	9.0	18.0	2.0
32.79	30.24	1.74	9.73	3.88	2.72	0.72	310.0	1.79	0.02	0.87	1.89	2.26	9.0	14.0	22
37.22	30.08	1.89	9.87	4.72	2.26	0.9	324.7	1.97	0.97	0.89	1.9	2.17	7.0	13.0	21

Continue Table (A- 1)

C ₁ S%	C ₂ S%	C ₃ A%	C ₄ AF%	MgO%	SO ₃ %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	AR	SM	IST (min)	FST (min)	f _r (MPa)
38.79	30.07	8.77	1.34	4.14	2.4	0.84	322.4	2.0	0.8	0.88	1.71	2.3	70	120	19.0
39.07	29.07	9.03	1.09	4.04	2.32	1	300.7	1.82	0.23	0.89	1.77	2.19	90	18.0	22
33.13	37.41	1.17	9.73	4.4	1.70	1.07	290.7	1.43	0.00	0.87	1.83	2.37	20	00	1.0
30.11	33.37	1.27	9.73	4.00	2.1	0.78	28.0	2.18	0.24	0.87	1.80	2.29	12.0	28.0	2.0
33.20	37.32	11.21	9.87	2.70	2.04	0.07	28.0	2.20	0.47	0.87	1.94	2.24	13.0	20.0	19.9
33.72	33.40	11.07	9.49	4.73	2.04	0.07	310	1.73	0.70	0.87	2.04	2.17	12.0	24.0	22.3
31.28	30	12.4	9.20	4.48	2.77	0.77	342	2.07	0.08	0.87	2.17	2.11	13.0	24.0	22.2
30.7	37.77	11.9	9.87	4.12	2.22	0.84	300.7	2	0.31	0.87	3.02	2.12	80	14.0	23.7
28.37	39.78	1.84	9.87	4.18	2.24	0.9	310.0	2.02	0.37	0.80	1.9	2.27	7.0	12.0	21
28.93	38.38	11.94	9.0	4.42	2.38	0.78	347.2	1.44	0.28	0.87	2.08	2.18	80	14.0	19.0
42.98	28.24	9.43	9.20	4.13	2.02	1.12	324.7	1.11	0.70	0.9	1.81	2.47	1.00	17.0	2.0
33.24	37.27	11.21	9.87	3.94	2.28	1.07	320.1	1.33	0.23	0.80	1.94	2.24	0.0	12.0	21.7
34.9	32.71	11.98	9.71	4.38	2.27	0.72	320	1.08	1.48	0.88	2.07	2.12	70	13.0	19.0
32.79	34.00	12.20	9.98	4.28	2.47	0.78	329	1.00	1.04	0.87	2.04	2.04	0.0	1.00	22.4
33.7	34	12.28	9.73	4.34	2.17	0.71	334	1.01	1.12	0.87	2.08	2.1	7.0	12.0	19.0
38.92	29.70	1.22	9.20	4.48	2.72	0.84	29.0	1.8	1.82	0.89	1.9	2.33	7.0	13.0	22.3
27.29	40.7	12.77	1.22	2.78	2.77	0.07	324.7	1.97	0.07	0.80	2.07	2.04	17.0	24.0	17.0
38.04	29.93	1.19	9.98	3.73	2.28	0.73	310.4	2.8	0.71	0.89	1.81	2.23	19.0	20.0	2.3
28.73	39.17	11.8	1.22	2.34	2.30	0.78	329	2.77	0.41	0.80	1.97	2.13	10.0	23.0	21.2
21.41	47.0	12.07	9.87	1.42	1.97	1.23	324.7	2.07	1.3	0.83	2.04	2.20	17.0	24.0	17.4
40.11	18.91	9.98	9.98	4.38	2.0	1	342.8	1.13	0.77	0.9	1.78	2.27	7.0	12.0	24.7
37.27	31.23	1.02	9.71	4.34	2.74	0.07	310.0	2.08	0.47	0.88	1.83	2.31	70	12.0	21
32.0	30.23	1.07	9.73	4.77	2.74	0.0	324.8	1.8	0.74	0.87	2.88	2.20	8.0	17.0	2.1
34.84	34.44	1.72	9.0	4.74	2.17	0.07	290	1.0	0.77	0.87	1.92	2.32	70	13.0	23.3

Continue Table (A- 1)

C ₁ S%	C ₂ S%	C ₃ A%	C ₄ AF%	MgO%	SO ₃ %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	AR	SM	IST (min)	FST (min)	f _r (MPa)
31.72	30.18	11.04	9.98	4.02	2.8	0.77	320.1	1.80	0.72	0.87	1.9	2.17	1.00	17.0	20.8

20.78	38.38	11.01	9.73	4.34	2.37	0.07	334	1.00	1.37	0.80	1.93	2.28	70	120	17.8
22.44	37.03	10.77	9.71	4.17	2.0	0.78	338	1.27	1.48	0.87	1.92	2.3	00	100	17
20.70	38.78	10.9	9.73	4.34	2.22	0.71	320	1.03	1.38	0.89	1.92	2.21	70	120	10.1
23.7	37.17	9.30	9.87	4.3	2.17	0.9	320	1.82	0.90	0.9	1.73	2.33	110	180	17.8
27.77	31.8	11.91	9.73	3.77	2.38	0.84	320	1.33	0.78	0.89	2.04	2.13	100	170	17.8
20.14	32.89	11.73	10.34	3.22	2.42	1.12	300.7	1.37	1.02	0.88	1.93	2.08	80	140	17
27.29	30.70	11.33	10.09	3.38	2.22	0.90	329.4	1.78	0.71	0.89	1.87	2.07	120	180	17.0
27.12	32.38	10.9	10.71	3.1	2.32	0.9	347	1.82	0.74	0.88	1.8	2.1	90	100	20
20.90	47.32	12.81	9.73	2.82	2.71	0.71	310.0	1.17	0.37	0.82	2.10	2.18	120	190	10.2
29.02	38.33	11.77	10.1	3.24	2.77	0.72	300.7	1.4	0.70	0.80	1.97	2.14	120	180	17
21.80	37.02	12.38	9.87	3.10	2.20	1.07	310.3	1.07	0.97	0.87	2.08	2.11	130	200	21.8
28.37	39.77	12.07	9.71	2.47	2.7	0.28	290.7	2.23	0.03	0.80	2.14	2.14	180	300	13.2
20.93	22.24	0.49	17.89	0.94	1.84	1.47	300.7	2.72	1.07	0.91	0.77	2.10	210	280	17.3
28.43	39.44	12.32	9.87	3.22	1.92	1.07	347.2	2.3	1.2	0.87	2.07	2.13	70	130	17.2
29.47	38.0	11.94	9.98	2.0	2.21	0.71	338.4	3.11	0.78	0.80	2.01	2.14	180	200	20.1
27.70	38.08	12.47	9.98	1.94	2.77	0.9	347.2	3.0	0.97	0.87	2.07	2.07	190	270	20.4
24.7	43.20	12.87	9.73	1.82	2.42	0.77	347.2	2.78	0.98	0.84	2.10	2.13	100	230	22.3
20.72	29.77	8.47	11.07	3.80	2.28	0.84	279	1.23	0.77	0.89	1.01	2.3	130	200	21.7
24.77	37.03	7.79	11.44	3.00	2.10	0.72	297	1.81	0.34	0.87	1.42	2.38	100	170	20.7
20.88	32.07	10.8	9.73	4.4	2.33	0.77	30.7	1.70	0.71	0.88	1.91	2.23	120	190	20
21.03	31.03	7.42	10.90	2.8	1.94	0.72	274.0	2.07	0.4	0.88	1.41	2.48	180	300	20.72
20.30	32.27	7.84	11.44	3.70	2.17	1	300.7	2.71	0.34	0.88	1.42	2.28	110	240	21.4
20.30	32.27	12.29	9.20	4.47	2.18	0.71	300.7	1.72	0.38	0.88	2.17	2.13	190	310	23.8

Continue Table (A-1)

C-S%	C-S%	C-A%	C-AF%	MgO%	SO ₂ %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	AR	SM	IST (min)	FST (min)	f _r (MPa)
20.19	37.14	7.07	9.49	4.80	2.00	0.77	300.7	1.81	0.37	0.87	1.99	2.23	170	280	21.8
22.37	37.12	11.04	9.49	4.02	2.28	0.07	333.9	1.74	0.34	0.87	1.97	2.27	120	210	23.4
23.71	28.90	3.93	13.01	3.73	2.14	1.07	310.3	1.40	0.31	0.88	0.97	2.47	120	210	20.3
27.79	32.08	9.42	10.22	4.38	2.14	0.72	342	1.70	0.43	0.87	1.79	2.32	110	190	22.2
23.77	34.71	9.00	9.98	4.77	2.47	0.72	313.9	1.3	0.01	0.87	1.73	2.33	100	170	24.7
20.13	38.22	10.04	9.87	4.88	2.7	0.84	311.7	1.21	0.39	0.80	1.8	2.33	80	100	21.0
21.22	29.48	8.29	11.78	4.02	2.11	0.90	319	1.03	0.07	0.89	1.40	2.22	100	170	22
24.07	32.00	11.07	8.88	4.37	2.37	0.78	279	2.1	0.01	0.87	2.07	2.32	120	170	22.7
23.44	34.92	9.84	10.1	4.87	2.42	0.90	319	1.27	0.71	0.87	1.77	2.27	140	200	21
21.28	37.72	11.27	9.87	4.38	2.37	0.07	327	1.48	0.49	0.87	1.90	2.2	100	100	23.27
20.90	37.07	12.12	8.88	4.70	2.12	0.71	322	2.10	0.4	0.87	2.9	2.23	90	140	20.2
20.44	37.13	10.34	10.47	4.21	2.71	0.07	310	1.30	0.39	0.87	1.77	2.19	120	180	24.8
23.07	20.07	8.37	11.07	0.2	2.24	0.77	300.7	1.21	0.42	0.9	1.0	2.23	120	180	21.2
27	32.77	9.07	10.34	4.9	2.04	0.07	310	1.30	0.39	0.87	1.7	2.27	120	180	24.8
23.31	38.11	0.97	12.03	3.93	2.17	1.12	377	1.17	0.29	0.80	1.7	2.40	100	210	20
22.90	34.83	10.40	9.98	3.17	2.08	1.23	347	2.31	0.34	0.87	1.84	2.23	80	104	20
27.13	41.74	11.02	9.20	4.80	2.40	0.78	338	1.89	0.72	0.84	2	2.34	130	190	19.2
27.07	32.48	9.29	9.98	2.72	2.71	1.78	30.1	1.8	0.01	0.89	1.7	2.37	130	200	18.3
20.78	39.74	9.70	9.20	3.9	2.20	0.78	320	1.82	0.37	0.80	1.80	2.03	80	270	18.1
20.87	38.07	9.30	9.0	4.70	2.03	0.77	334	2.28	0.30	0.80	1.77	2.0	140	200	21
24.90	43.1	10.07	9.98	2.93	2.7	1.29	342	2.43	0.74	0.84	1.80	2.3	80	100	17
27.97	29.77	10.09	9.49	4.27	2.32	0.78	320	3.40	0.37	0.89	1.87	0.24	120	220	22.3
27.27	39.23	12.21	9.49	3.93	2.74	0.89	320	2.07	0.47	0.80	2.11	2.14	90	190	23.8

1.78	27.73	8.40	9.87	4.72	2.0	0.78	320	2.39	0.23	0.89	1.72	2.43	80	200	21
------	-------	------	------	------	-----	------	-----	------	------	------	------	------	----	-----	----

Continue Table (A- 1)

C-S%	C-S%	C-A%	C:AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	MA	SM	IST (min)	FST (min)	f _r (MPa)
27.27	41.3	12.44	9.73	2.7	2.78	1.12	330	1.12	0.97	0.80	2.1	2.14	90	200	17
44.72	44.27	9.29	9.98	2.78	2.70	0.89	400	2.39	0.07	0.83	1.7	2.47	00	170	20
33.43	30.21	9.18	11.2	4.07	2.18	0.78	320	2.92	0.70	0.87	1.79	2.38	90	240	23.0
38.42	38.20	11.33	9.73	4.1	2.28	0.72	300	2.97	0.01	0.87	1.97	2.18	120	220	20.0
34.00	34.31	7.97	11.19	4.4	2.11	0.90	320	2.74	0.42	0.87	1.40	2.33	120	240	23
27.27	31.18	10.47	9.0	4.4	2.34	0.71	374	2.38	0.00	0.88	1.9	2.20	120	240	23
34.73	34.14	10.12	9.20	4.07	2.24	0.77	339	2.77	0.8	0.87	1.89	2.38	110	230	27.3
27.04	27.72	8.30	9.87	3.97	2.19	0.78	307	2.87	0.47	0.9	1.71	2.42	100	270	20
41.1	29.7	7.7	13.39	2.43	1.94	0.84	277.8	2.01	0.4	0.88	1.21	2.17	100	180	19.8
34.72	34.77	10.17	8.88	4.03	2.7	0.77	332	1.08	0.39	0.87	1.90	2.47	130	270	22.4
30.77	38.33	11.17	8.02	4.73	2.19	0.07	310.7	2.07	0.37	0.80	2.14	2.43	120	230	23.0
37	31.0	7.41	12.78	4.0	2.13	1.12	287.0	1.70	0.4	0.88	1.3	2.14	90	180	20.7
30.08	38.07	8.91	11.32	3.7	2.13	0.90	340	2.04	0.37	0.80	1.04	2.27	40	100	24.2
27.79	32.08	9.42	10.22	4.38	2.14	0.72	342	1.70	0.43	0.87	1.79	2.32	110	190	22.2
33.33	34.77	10.2	11.2	3.80	2.07	0.78	329.4	1.17	0.30	0.88	1.78	2.11	130	200	23.8
38.29	39.7	11.08	9.71	4.01	2.41	0.89	274.0	1.43	0.29	0.80	1.97	2.27	130	190	21.8
00.78	19.11	0.08	17.08	1.7	2.10	1.78	298	0.04	0.78	0.93	0.74	2.3	100	240	23.2
01.71	21.93	1.70	17.7	1.72	2.1	1.47	300.7	0.77	0.73	0.92	0.70	2.21	140	230	21.3
41.02	27.04	10.00	9.87	4.73	2.7	0.91	313.3	1.22	0.34	0.9	1.81	2.24	100	220	21.0
30.38	34.71	8.78	9.87	4.19	2.44	0.9	291.0	1.19	0.73	0.87	1.77	2.48	100	190	20
30.09	33.91	11.07	9.72	3.2	2.04	1.42	398.4	1.24	0.00	0.89	1.99	2.28	100	170	21.8
27.81	41.18	10.34	9.13	3.1	2.73	1.14	310	2.1	1.1	0.83	1.94	2.47	100	190	18.9
24.84	42.97	9.91	9.09	3.1	2.77	1.27	313.7	2.8	0.89	0.82	1.83	2.42	100	210	17.7
38.30	32.02	0.24	12.24	2.77	2.42	1	300	2.3	0.82	0.87	1.13	2.87	130	230	20.7

Continue Table (A- 1)

C-S%	C-S%	C-A%	C:AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	MA	MS	IST (min)	FST (min)	f _r (MPa)
29.77	38.04	11.27	9.37	3.97	2.37	1.12	310	1.7	1.2	0.80	2.02	2.27	110	210	18
27.09	29.09	11.24	8.77	4.48	2.38	0.9	300	2.2	1.1	0.88	2.11	2.24	120	220	19.0
27.08	30.28	10.18	9.73	4.1	2.74	0.90	311.0	2.02	0.74	0.88	1.92	2.17	100	240	19
02.02	19.09	2.42	13.39	2.70	2.3	1.12	320.7	2.48	1.1	0.91	0.93	2.44	100	180	18.7
41.93	28.70	7.07	10.1	3.07	2.7	1.28	304.7	2.43	1.17	0.80	1.38	2.70	120	240	18.4
43.7	22.70	0.04	10.90	3.00	2.77	1.2	300.7	2.70	1	0.89	1.17	2.78	100	230	18
32.02	32.02	8.97	9.71	4.03	2.7	1	299.8	1.99	0.90	0.87	1.7	2.47	100	180	18.2

Table (A- ٢) Properties of Sulfate Resisting Portland Cements form Data Obtained by Consultant Engineering Bureau in University of Babylon (for The Period between ٢٠٠٠-٢٠٠٣)

No.	C+S%	C+S%	C+A%	C:AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	IST (min)	FST (min)
١	٤١.٣٢	٢٩.٨٩	٣.٤٦	١٥.٢١	٢.٤	٢.١٦	٠.٨٩	٣٥٥.٧	٢.٨٥	٠.٦	٠.٨٧	١٨.	٢٦.
٢	٥١.١٣	٢٢.٧٨	١.٧٦	١٤.٨٥	٢.٨٥	٢.٠٥	٠.٧٢	٣٣٤	٢.١١	٠.٥٣	٠.٩	١٢.	٢٤٥
٣	٤٩.٤٣	٢٣.٧٧	٠.٩٨	١٥.٥٨	٣.١٧	١.٩١	١	٢٧٥	٢.٢٥	٠.٢٣	٠.٩	١٢.	٢٤.
٤	٤٧.٨	٢٥.٤	٣.٤٣	١٤.٦	٢.٣٤	٢.١	١.٠٦	٣٣٨	١.٤٧	٠.٢٩	٠.٩	١٢.	٢٢٥
٥	٤٧.٦٨	٢٥.١	٢.٧١	١٦.١٩	١.٤٧	٢.١٧	٠.٨٤	٣٣٤	٢.١١	٠.٦٣	٠.٩	١٣.	٢٤.
٦	٥٣.١٣	١٩.٧٨	١.٦٧	١٥.٥٨	٣.٠٨	١.٩٦	٠.٦٧	٣٣٤	٢.٦٢	٠.٥٨	٠.٩١	١٢.	٢٤.
٧	٥١.٥٣	٢٢.٢٥	٠.١٢	١٧.٠٤	٣.١٨	٢.٠١	٠.٨٤	٣٢٠	١.١٥	٠.١١	٠.٩	١٤٥	٢٤.
٨	٤٤.٧١	٢٨.٤٨	١.٧٩	١٦.٧٩	١.٩٥	٢.٠٥	١	٣٤٧	١.٥٣	٠.٤٣	٠.٨٨	١٤.	١٩٥
٩	٥١.٢	٢١.٥٨	١.٨٧	١٥.٧	٣.٤٢	٢.١١	٠.٦٧	٣٢٩	١.٧٣	٠.٤٥	٠.٩١	٩.	١٨.
١٠	٤٩.٩١	٢٣.٧٦	٣.٣٥	١٥.٢١	١.٦١	٢.١٥	٠.٧٨	٣٢٢	١.٤	٠.٦٨	٠.٩	١٢.	١٩.
١١	٥٦.٣٣	١٥.٧	٣.٤٦	١٥.٧	١.٧٨	٢.٠٧	٠.٨٩	٣٥٦	١.٨١	٠.٥٧	٠.٩٤	٩.	١٩.
١٢	٥٨.٢٢	١٦.٥٧	.	١٦.٥٥	٢.٩٧	١.٩٢	٠.٨٩	٣٣٤	١.٣٨	٠.٥٢	٠.٩٣	١٢.	١٨.
١٣	٥٩.٣٨	١٤.٧٧	١.٤٧	١٥.٩٤	١.٧٢	٢.٢٦	٠.٨٤	٣١٥.٥	١.٥٦	٠.٤٥	٠.٩٤	١٣٥	١٩.
١٤	٦٢.١٧	١٤.٢٨	.	١٦.٠٦	١.٧	٢.١١	٠.٦٧	٣١٥	١.٢٥	٠.٤٦	٠.٩٣	١٢٥	١٩.
١٥	٥٩.٢	١٥.٧٢	٢.٥٣	١٤.٦	٢.٣٥	٢.٠٣	٠.٥٦	٣٢٩	١.٤٣	٠.٢٨	٠.٩٣	١٢.	١٨.
١٦	٥٥.٥٤	١٩.٤٥	٢.٩٣	١٤.٣٦	١.٩	٢.١٤	٠.٥	٣٢٩	١.١٥	٠.٣٩	٠.٩١	١٢.	١٩.
١٧	٥٥.٦٢	١٨.٩٣	١.٨٦	١٥.٣٣	٣	٢.٠٢	٠.٢٨	٣٦٨	١.١٢	٠.٥٣	٠.٩١	١١.	١٧.
١٨	٣٣.٧٤	٣٥.٤٩	١١.٣	٧.٧٩	٣.٣٥	٢.١٥	٠.٣٣	٣٥٦	٢.٨٦	٠.١٧	٠.٨٧	١٢.	١٩٥
١٩	٥١.١٨	٢٣.٣٧	١.٣	١٥.٥٨	١.٦٨	٢.٢	١.١٢	٣٠.٦	١.٦٧	٠.٣١	٠.٩	١٢٥	٢١.
٢٠	٥٩.٥١	١٥.٣٧	٠.٠١	١٥.٩٤	٢.٩٢	١.٨٨	٠.٧٢	٣٢٠	١.٦١	٠.٢	٠.٩٣	١٢.	٢٠.
٢١	٥٧.٠٥	١٧.٥١	٠.١٣	١٥.٥٨	٢.٥٥	٢.٠٧	٠.٦٧	٣١٠	٢.٢٥	٠.٦١	٠.٩٢	٩.	١٩.
٢٢	٥٥.٢	١٨.٣٣	٠.٣٩	١٦.٠٦	٢.٩٥	٢.١	٠.٦٧	٣٠.٦	١.٩٥	٠.٣٩	٠.٩٢	١٣.	٢٤.
٢٣	٥٨.٩٣	١٦.٢	.	١٦.٠٦	٣.٢	١.٨٧	٠.٧٣	٣٠٠.٦	١.٥١	٠.٤٢	٠.٩٣	١١.	١٨.

Continue Table (A- ٢)

No.	C+S%	C+S%	C+A%	C:AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	IST (min)	FST (min)
٢٤	٥٨.٣٤	١٦.٦٥	٠.٠١	١٥.٧	٢.٧٣	١.٩٨	٠.٧٨	٣٤٠	١.٧٥	٠.٣٣	٠.٩٣	٨.	١٧.
٢٥	٣٦.١٩	٣١.١٢	١٠.٤٧	١١.٢	٣.٣٣	١.٩٢	٠.٧٢	٣١٣	٣.٣٥	٠.٣٥	٠.٨٨	١٢٥	٢٠.
٢٦	٥٤.١٥	١٩.٨١	٢.٥٥	١٥.٧	١.٧٥	١.٨٦	٠.٦٧	٢٨٠	١.٩٧	٠.٣٩	٠.٩٢	١٢.	٢٢.
٢٧	٦٠.٦٩	١٤.٣	٠.٦٧	١٤.٦	٢.٨٥	٢	٠.٦١	٣٠٠	٢.٢٧	٠.٣٧	٠.٩٤	٩.	٢٠.

28	02	22.29	0.29	14.73	2.24	2.12	0.77	300	3.40	0.40	0.9	120	230
29	40.97	32.37	2.00	10.78	1.19	2.27	0.72	310.8	1.40	0.0	0.88	170	240
30	70.87	14.37	-0.28	17.18	3.11	2.07	1.80	379.4	1.47	0.43	0.93	110	230
31	08.07	17.00	0.01	10.82	1.91	2.14	0.37	281.8	1.74	0.49	0.92	120	240
32	48	27.71	-1.37	10.8	2	2.12	0.02	284.4	2	0.70	0.87	120	210
33	47.98	27.27	-1.03	17.12	2.0	2.09	0.0	311.7	2.3	0.07	0.87	120	200
34	49.70	20.04	-0.90	17.04	2	2.00	0.0	317.3	2	0.04	0.88	80	180
35	40.01	27.48	2.99	10.08	2.21	2.1	0.81	300.7	1.73	0.29	0.88	120	210
36	01.1	23.77	0.73	17.17	1.22	2.03	0.78	324	1.94	0.47	0.9	170	270
37	48.44	20.00	1.78	10.94	3.02	1.82	0.84	320.1	1.17	0.13	0.89	70	140
38	48.44	20.00	1.78	10.94	3.02	1.82	0.70	320.1	1.17	0.13	0.89	70	140
39	47.02	27.03	3.11	10.40	3.04	2.02	0.70	300	1.01	0.00	0.88	130	300
40	47.44	27.77	2.73	17.43	1.03	1.87	0.71	300	1.9	0.41	0.89	120	280
41	00.00	21.90	3.37	10.21	3.72	1.80	0.89	301.0	0.80	0.17	0.91	70	140
42	01.8	21.13	2.77	10.21	3.94	1.74	0.78	310.0	1.12	1.2	0.91	90	140
43	40.74	27.98	2.84	17.43	1.84	2.12	0.84	300.7	1.00	1.21	0.89	90	100
44	43.70	28.23	2.84	10.1	3.11	2.08	0.9	347.2	1.87	0.81	0.89	180	200
45	48.00	20.80	0.02	18.27	0.72	2.18	1.34	342.8	1.70	0.73	0.9	70	120
46	02.28	21.40	2.77	10.21	3.4	1.98	1.01	324.8	0.82	0.74	0.91	110	190
47	01.87	22.07	1.98	17.00	1.42	2.22	0.07	320	1.1	0.47	0.91	IST	100

Continue Table (A- 2)

C _r S%	C _s S%	C _r A%	C _r AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	IST (min)	FST (min)	AR	SM	f _r (MPa)
19.30	19.30	3.32	10.1	3.2	2.17	0.84	329	1.0	0.37	0.92	90	180	0.89	2.21	17.0
01.04	22.41	2.07	17.04	0.70	2.17	1	307	1.08	0.81	0.91	130	180	0.78	2.14	17
03.42	18.99	3.02	10.82	3.0	2.17	1.07	329	1.13	0.77	0.92	130	210	0.80	2.14	22.0
08.07	24.88	1.00	17.70	1.1	2.3	1.07	338.4	1.11	0.77	0.9	120	180	0.7	2.17	19
07.02	20.3	3.3	10.21	3.07	2.08	1.01	310.0	0.90	0.83	0.9	80	140	0.88	2.24	20.7
00.23	29.12	.	17.9	0.70	2.47	1.47	338.4	1.23	0.41	0.88	100	230	0.73	2.3	19.2
03.12	29.01	3.49	14.97	2.9	1.8	1.34	340.7	1.42	0.72	0.88	200	290	0.9	2.3	27
03.20	27.07	3.47	14.72	3.24	2.00	1.4	300.7	3.34	1.08	0.89	210	300	0.91	2.20	20.2
00.27	22.17	3.40	14.80	3.30	2.02	1.28	301	1.28	0.47	0.91	120	180	0.9	2.20	30.7
04.00	29.84	3.20	10.21	1.41	2.11	0.9	301	1.23	0.72	0.88	90	170	0.88	2.23	20.4
00.31	17.72	2.78	10.08	1.40	2.11	0.90	280	2.43	0.71	0.93	190	310	0.84	2.19	20.0
09.42	22.79	2.17	14.97	3.20	2.13	0.78	300.7	2.43	0.47	0.9	90	270	0.8	2.30	20.3
09.77	24.43	.	17.77	3.27	1.87	0.89	388	1.27	0.29	0.89	70	180	0.73	2.4	27.07
07.30	27.93	3.48	10.09	1.40	2.27	0.9	300.7	1.13	0.40	0.88	70	180	0.9	2.22	19.0
00.97	18.77	0.47	10.1	3.00	1.92	0.84	344	1.27	0.18	0.92	120	190	0.77	2.07	28.0
03.23	21.73	0.7	17.07	1.7	2.18	1	310	1.70	0.47	0.91	110	170	0.78	2.43	20
00.78	28.03	0.03	17.77	2.1	2.13	0.84	340	1.73	0.08	0.87	120	180	0.77	2.39	22.7
00.73	27.72	3.48	10.09	3.8	1.87	0.78	338	0.89	0.30	0.89	140	240	0.9	2.27	24.1
01.03	22.20	0.12	17.04	3.18	2.01	0.90	320	1.10	0.11	0.9	140	240	0.27	2.31	22
04.71	28.48	1.79	17.79	1.90	2.00	0.84	347	1.03	0.43	0.88	140	190	0.77	2.23	20
09.43	23.77	0.98	10.08	3.17	1.91	1	270	2.20	0.23	0.9	120	240	0.71	2.43	24.0
07.8	20.4	3.43	14.7	2.34	2.1	1	338	1.47	0.29	0.9	120	220	0.9	2.34	20.1
07.78	20.1	2.71	17.19	1.47	2.17	1.07	334	2.11	0.73	0.9	130	240	0.83	2.18	19.0
01.32	29.89	3.47	10.21	2.4	2.17	0.84	300.7	2.80	0.7	0.87	180	270	0.9	2.24	22

Continue Table (A- ٢)

No.	C _r S%	C _s S%	C _r A%	C _r AF%	MgO%	SO _r %	Free CaO%	S _s (Blaine) (m ² /kg)	L.O.I.%	IR%	L.S.F.%	IST (min)	FST (min)
٧٢	٥١.١٣	٢٢.٧٨	١.٧٦	١٤.٨٥	٢.٨٥	٢.٥	٠.٨٩	٣٣٤	٢.١١	٠.٥٣	٠.٩	١٢٠	٢٤٥
٧٣	٥٣.١٣	١٩.٧٨	١.٦٧	١٥.٥٨	٣.٠٨	١.٨٦	٠.٧٢	٣٣٤	٢.٦٢	٠.٥٨	٠.٩١	٦٠	٢٤٠
٧٤	٥٤.٠٥	٢١.٥	٠.٣١	١٥.٨٢	١.٦٨	١.٩٣	٠.٦٧	٢٨٧.٥	٢.٢	٠.٣٦	٠.٩	١٣٠	٢٢٠
٧٥	٥٥.٣	١٧.٣٤	٣.١٦	١٥.١	٣.١٥	١.٩	٠.٧٢	٣٤٤.٢	١.٦٨	٠.٣٤	٠.٩٣	١٢٠	٢٣٠
٧٦	٥١.٥٦	٢١.٠٢	٣.٤٩	١٤.٩٧	٣.٢٦	١.٩٨	٠.٨٩	٣٨٩.٣	١.٣٢	٠.٤٧	٠.٩١	٩٠	١٨٠
٧٧	٥٦.٦٨	١٩.١٦	٢.٣٤	١٤.٣٦	١.٤١	٢.١٤	٠.٨٤	٣٠١.٥	١.٢١	٠.٦٨	٠.٩٢	١٢٠	١٨٠
٧٨	٤٥.٠٤	٢٩.٩٥	٢.٥٨	١٤.٦	١.٦٦	٢.٣	٠.٧٨	٣٢٠	١.٠٥	٠.٤٩	٠.٨٨	٩٠	١٥٠
٧٩	٤١.٦٨	٣١.٢٢	٢.٦٦	١٥.٧	٣.٤٥	٢.٠٣	٠.٨٩	٣٥١.٥	٠.٩٣	٠.٣٢	٠.٨٧	١٣٥	٢٠٠
٨٠	٣٩.٤٦	٣٣.٠٢	٠.٤٩	١٦.٥٥	١.٨٢	٢.١٣	٠.٦٧	٢٦٩	٢.٧	٠.٦٥	٠.٨٥	١١٠	٢١٥
٨١	٣٨.٧٥	٣٤.٢٤	٠.٤٣	١٥.٩٥	٢.٣٧	٢.١٢	١.٥	٣٠٠.٥	٢.٦	٠.٨٥	٠.٨٤	٨٠	١٩٠
٨٢	٦٦.٠١	٧.٤٢	-١.٦٨	١٧.٠٤	٢.٤٢	٢.١٣	١.٣	٣٠٣	٢.٨٧	٠.٩٥	٠.٩٦	١١٠	٢٤٠
٨٣	٤٩.٨	٢٤.٧٦	-٠.٦٦	١٧.٤	٢.٠٣	٢.١٧	١.٤	٣٢٠.١	١.١٢	٠.٧٧	٠.٨٨	١١٥	٢٢٠

Table (A- ٢) Properties of The Cements from Data Obtained by AL-Ta'ii (٢٠٠١)

C+S%	C+S%	C+A%	C:AF%	MgO%	SO _r %	L.O.I.%	IR%	L.S.F.%	S _s (Blaine) (m ² /kg)	Unsoundness%	IST (min)	FST (min)	f _v (MPa)
26.2	40.7	8.99	9.8289	3.20	2.03	1.10	0.44	0.81	307	0.16	140	210	27.2
23.3	0.	8.17	9.4942	2.71	2.47	1.48	0.40	0.8	344	0.16	200	260	26.1
26	43	11.7	9.0987	3.20	2.43	1.87	0.40	0.82	300	0.07	170	240	26.8
40.0	32.0	8.18	9.129	3.01	2.0	1.1	0.7	0.87	374	0.16	120	200	37.0
29.7	42.1	10.1	9.7072	2.71	2.27	1.10	0.74	0.83	300	0.03	120	170	31.4
34.3	39.8	8.98	9.7473	2.72	1.94	0.87	0.72	0.84	371	0.02	130	200	34.7
39.8	34.7	8.01	9.7377	2.01	2.01	0.81	0.44	0.89	347	0.04	140	190	36.2
04.2	18.7	7.03	9.4333	2.0	2.44	1.00	0.38	0.87	330	0.18	120	170	24.3
27.8	42.4	10.4	9.981	4.24	2	0.92	0.04	0.83	321	0.79	80	130	26.7
20.0	47.7	12.8	9.7109	4.17	2.0	1.28	0.72	0.88	327	0.12	140	220	27.4
33.8	37.8	9.01	9.7072	4.24	2.3	0.77	0.98	0.84	321	0.38	130	160	26.8
31.9	38.7	10.1	9.7377	4.31	2.23	0.8	0.0	0.82	383	0.03	80	100	38.0
20.4	00.7	10.9	9.7109	2.47	2.4	0.7	1.3	0.8	301	0.22	100	210	22.1
30.2	33.9	12.7	9.4737	3.98	1.92	0.97	1.27	0.87	310	0.0	70	110	27
33.4	34.8	11.3	9.7377	4.82	2.4	1.10	0.7	0.87	290	0.28	70	110	20.1
32.4	37.9	9.9	10.103	4.07	2.43	1.71	0.72	0.80	310	0.16	137	183	24.4
33.4	34.9	12.7	9.4942	2.03	2.47	1	1.3	0.87	327	0.19	140	180	27.8
20.7	48.7	11.7	9.8093	2.1	2.71	1.4	0.9	0.81	279	0.1	170	230	21.9

Continue Table (A-7)

C+S%	C+S%	C+A%	C:AF%	MgO%	SO _r %	L.O.I.%	IR%	L.S.F.%	S _s (Blaine) (m ² /kg)	Unsoundness%	IST (min)	FST (min)	f _v (MPa)
31.7	37.8	10.3	10.781	4.00	2.71	0.73	0.43	0.80	321	0.10	70	120	23.7

27.3	39.8	12.2	1.200	2.40	2.78	1.0	0.0	0.84	317	0.04	160	200	23.0
37.0	33.7	8.73	9.8093	3.7	2.0	1.0	0.0	0.87	277	0.01	100	130	27.7
24.8	47.9	9.77	8.277	3.8	2.03	0.81	0.37	0.8	334	0.13	200	260	32.8
29.0	37.3	10.3	8.2460	3.04	2.07	1.20	0.37	0.87	339	0.12	189	230	18.7
19.8	00.2	12.7	7.8814	2.09	2.37	1	1.3	0.8	270	0.0	170	270	27.1
37.0	31.4	11.8	7.7784	2.01	2.03	1.7	1	0.88	289	0.02	170	240	29.7
33.7	40	9.08	8.7117	3.37	2.27	0.37	0.02	0.84	339	0.02	70	110	31
27.2	44.1	11.2	8.7117	3.0	2.34	0.74	0.49	0.82	327	0.19	70	130	27.1
20	03.2	9.14	8.7421	2.01	2.21	0.73	0.0	0.78	317	0.03	70	120	31.8
32.1	37.4	12.3	9.0073	2.03	2.44	1	1.2	0.80	283	0.24	190	200	27.4
34.4	37.7	12.1	8.49	2.44	1.87	0.90	0.47	0.87	297	0.07	240	277	27.2
31.0	41	9.0	8.7738	3.01	1.97	1.7	1	0.83	282	0.17	100	220	24
17.9	00.7	14.7	8.8807	2.90	2.09	0.78	0.7	0.8	290	0.11	140	180	19.8
28.7	39	13.9	9.129	3	2.39	0.92	0.77	0.80	297	0.00	180	220	20.9
27.3	42.1	13.1	8.7738	3.13	2.31	0.07	0.48	0.83	317	0.17	120	190	27.9
41.4	33.4	8.77	8.0204	2.04	1.83	1.0	0.43	0.87	339	0.08	140	190	37
39.4	32.0	11.2	8.0330	3.1	2.27	1.17	0.34	0.87	344	0.17	240	330	20
39.8	31.7	9.23	8.3987	3.22	2.71	1.8	1.2	0.87	308	0.13	220	310	30

Continue Table (A-7)

C _r S%	C _r S%	C _r A%	C _r AF%	MgO%	SO _r %	L.O.I.%	IR%	L.S.F.%	S _s (Blaine) (m ² /kg)	Unsoundness%	IST (min)	FST (min)	f _v (MPa)
30.4	42.7	9.00	8.0204	2.9	2.04	1.01	1	0.83	292	0.27	100	210	27.1
33.7	39.1	11.3	8.0204	2.81	1.90	1.3	0.07	0.88	300	0.07	00	110	38
33.3	38.4	12	8.7421	3.02	1.73	1.11	0.73	0.80	310	0.10	00	100	28.2
27.8	42.9	11.1	9.0073	2.73	2.71	1.17	0.03	0.83	340	0.12	00	90	27.0

28.7	23.1	11.3	9.8093	1.20	2.10	0.8	1.1	0.83	3.2	0.2	120	210	27.3
31.9	37	11	9.7463	2	2.2	1.20	1.7	0.80	297	0.32	190	220	27.3
37	32.7	11.2	9.8093	2.21	1.72	1.1	0.21	0.87	310	0.73	80	120	29.9
36.2	32.8	10.8	10.237	2.27	2.02	1	0.01	0.87	333	0.22	80	120	29.9
31.2	37.2	10.0	9.9007	2.29	2.72	1.02	0.82	0.82	303	0.32	120	200	20.1
32.0	32.2	12.1	10.200	2.08	1.17	0.88	0.07	0.87	301	0.12	120	180	27.9
33.8	36.2	10.9	9.8289	2.32	1.9	1.02	0.7	0.80	310	0.37	120	210	30.1
32.8	30.7	10.7	9.7376	2.28	2.0	1.23	0.07	0.80	309	0.2	90		20.7

Table (A-4) Properties of The Cements from Data Obtained by AL-A`araji (2003)

N o.	C _r S %	C _s S %	C _r A %	C _i A F%	Mg O%	SO r%	Free Ca O%	L.O.I .%	IR %	L.S.F .%	S _s (Blaine) (m ² /kg)	IST (min)	FS T (min)	f _r (MP a)	f _v (MP a)	f ₂₈ (MP a)
1	28.9	38.10	11.17	8.022	2.73	2	0.07	1.3	0.37	0.80	310.7	12	23	23	31.0	20.0
2	30.77	32	12.29	9.20	2.27	2	0.71	1.32	0.38	0.88	300.7	19	31	23	29.7	27.0
3	32.08	33.87	11.72	9.80	2.8	1.9	0.77	2.02	0.29	0.87	300.7	12	27	22	28.7	23.2
4	29.01	29.2	9.38	9.28	2.73	2	0.71	1.27	0.01	0.89	290.7	19	27	22.9	33.2	27.7
5	38.00	29.9	11.10	10.32	2.20	2.2	0.71	1.78	0.39	0.89	307	12	22	22	30	22.0
6	29.	30.1	8.2	10.1	2.3	2.2	0.7	2.27	0.	0.88	280	10	22	20	29.	28.

	12	7	8	0	7	4	7		0			0	0		0	0
7	38.00	30.87	9.97	10.10	3.70	2.27	0.84	1.9	0.00	0.88	310	110	180	23	29.0	43.8
8	34.33	34.81	11.21	9.80	3.17	2.23	0.72	1.13	0.44	0.87	320	130	190	21.0	28	43
9	42.88	27.20	8.27	9.82	4.24	2.33	0.77	1.8	0.00	0.89	320	110	180	20.7	29	47.0
10	30.14	31.07	12.03	9.80	3.81	2.32	0.72	1.8	0.48	0.88	324	120	180	20	28.7	47.7
11	32.12	30.10	11.04	9.82	4.31	1.90	0.77	1.38	0.39	0.87	310	180	260	23.0	32.7	43.0
12	37.90	30.817	9.87	9.71	4.73	2.30	0.84	2	0.33	0.88	300.7	170	280	21.0	28	44.1
13	30.43	37.97	11.20	9.49	4.80	2.00	0.77	1	0.37	0.87	300.7	170	280	21.1	29.4	44.8
14	43.44	34.08	10.17	8.88	4.03	2.37	0.77	1.13	0.39	0.87	332	130	260	23	29.7	47.2
15	30.00	32.04	7.84	11.44	3.70	2.22	1	1.9	0.34	0.88	300.7	110	24	22	28	44.7
16	37.29	31.19	7.41	12.78	4.00	2.21	1.1	1.7	0.44	0.88	287.0	90	180	21.7	29	47.70
17	30.17	30.77	8.44	10.71	3.33	2	1.07	1.32	0.3	0.87	300.7	170	290	21	29.1	40.1
18	30.91	33.78	7.90	11.31	4.17	2.18	0.77	1.40	0.27	0.87	329.4	100	210	24.0	32.8	44
19	41.77	28.91	7.77	11.07	3.91	2.34	0.84	1.81	0.44	0.88	324	130	190	24.7	28.8	48.4
20	43.47	28.03	7.07	10.83	3.78	1.9	0.77	1.77	0.41	0.89	320	100	180	20.2	32.0	49.41
21	39.28	32.83	0.47	12.00	3.77	1.91	0.77	1.2	0.71	0.87	310	100	170	27.1	31.8	49.8
22	23.09	47.04	8.89	9.73	3.00	2.49	0.77	1.70	0.40	0.81	309	200	270	21.73	31.7	48.1
23	23.27	49.82	8.83	9.43	2.82	2.10	0.80	1.87	0.41	0.8	340	130	210	22	31.71	49.2
24	44.02	27.77	9.08	9.40	2.72	2.11	0.77	1.4	0.7	0.9	304	170	230	20.87	31.8	47.9
25	44.74	28.00	7.92	9.71	2.81	1.97	0.84	1.0	0.40	0.89	370	120	200	24.9	32	48.0

Continue Table (A-4)

N O.	C ₁ S %	C ₂ S %	C ₃ A %	C ₄ A F%	Mg O%	SO ₃ %	Free Ca O%	L.O.I .%	IR %	L.S.F .%	S _s (Blaine) (m ² /kg)	IST (min)	FS T (min)	f ₁ (MP a)	f ₂ (MP a)	f _{2.8} (MP a)
26	21.07	49.70	9.17	9.09	3.23	2.42	0.8	2	0.44	0.8	300	110	178	20	31	47.1
27	00.02	21.20	8.10	9.10	2.79	2.10	0.7	1.7	0.73	0.92	370	141	207	20.0	33	49
28	00.47	21.83	7.71	9.12	2.71	2	0.09	1.99	0.73	0.92	349	100	191	20.7	34.2	48
29	20.31	01.84	9.23	8.40	4	2.39	0.9	0.9	0.4	0.8	310.8	70	120	20	28	47.0

3	24.	47.	11.	8.00	2.9	2.0	0.9	1.40	0.	0.82	339	70.	11	22.	31	49.
0	14	29	11			2	7		49				7	13		9
3	20.	01.	9.1	8.08	4	2.3	0.8	1.0	0.	0.8	329	72	13	20.	29	47.
1	82	27	4			1	8		40				0	0		7
3	27.	30.	12.	8.24	2.8	2.7	0.7	1.0	0.	0.89	340	18	23	24	22.	49
2	07	72	74			1	1		01						2	
3	24.	47.	9.3	8.21	3.9	2.2	0.8	1.3	0.	0.81	330	19	20	22.	30.	47.
3	49	49	7			1	9		42				0	1	7	0
3	30.	42.	9.0	8.71	3.0	2.0	0.8	1.2	0.	0.82	300	17	27	23	30.	49.
4	74	10	1				2		01				7	0	9	7
3	22.	30.	11.	7.91	2.7	2.2	0.7	1.3	0.	0.87	288	17	24	22.	31.	47.
0	29	70	73			8	7		39				0	2	4	2
3	28.	30.	8.7	8.40	2.9	1.9	0.7	1.07	0.	0.87	330	14	19	22.	30.	44.
7	78	10	2			1	7		70				0	0	30.	30
3	27.	34.	10.	8.10	2.0	2.2	0.7	1.22	1.	0.87	300	24	22	21.	30.	47
7	27	79	94			0	8		10				1	1	7	
3	29.	31.	9.2	8.30	2.7	1.8	0.8	1.20	0.	0.88	307	23	31	23.	31.	47.
8	30.	30.	1			9			41				0	78	2	1
3	30.	41.	9.0	8.02	2.9	1.7	0.7	1.7	0.	0.84	290	10	21	20.	29.	47.
9	07	40	4			0	2		33				2	9	8	7
4	31.	39.	11.	8.08	2.9	1.9	0.7	1.32	0.	0.80	300	70.	11	22	30.	40.
0	47	30	90			0			70				0		2	3
4	28.	32.	11.	8.40	2.8	1.9	0.7	1.1	0.	0.88	320	04	10	21.	20.	47.
1	38	39	19			9			97				7	3	7	2
4	40.	29	10.	8.18	2.0	1.9	0.8	1.01	0.	0.89	340	70.	97	14.	31.	49.
2	07		92						40					2	7	3
4	31.	39.	11.	8.02	2.0	2.1	0.7	1.7	0.	0.80	310	10	19	20.	27.	43.
3	10	87	90			2	7		90				3	2	1	0
4	27.	44.	9.4	8.82	2.8	1.8	0.8	1.70	0.	0.82	280	19	20	20.	29.	47.
4	77	07	0			8	7		0					20.	41	0
4	19.	48.	14.	8.79	3	2	0.8	1.2	0.	0.82	300	23	28	19.	27.	47.
0	02	79	07				9		72					7	74	7
4	24.	44.	12.	8.00	2.8	1.8	0.8	1.41	0.	0.82	289	17	23	20.	28.	40.
7	49	02	94			0	9		00					20.	84	9
4	27.	40.	13.	9.03	2.7	1.9	0.8	1.1	0.	0.80	291	13	18	20.	28	47.
7	02	89	84			1	7		7				9	27		0
4	22.	37.	11.	8.02	2.0	1.9	0.8	1.12	1.	0.87	320	12	19	20.	28.	43.
8	44	02	79			0			1				1	3	1	8
4	29.	38.	12.	8.94	2.7	1.8	0.8	1.02	0.	0.80	298	17	22	21	29.	47
9	78	91	19			7	3		01				0	2	18	
0	27.	41.	10.	10.0	4.3	1.9	1.1	1.77	0.	0.84	310.	10.	12	20.	28.	47.
0	07	93	84	4	8	1			78		4		3	43	8	1

Continue Table (A-4)

N O.	C _r S %	C _r S %	C _r A %	C _s A F%	Mg O%	SO _r %	Fre e Ca O%	L.O.I .%	IR %	L.S.F .%	S _s (Blaine) (m ² /kg)	IST (mi n)	FS T (mi n)	f _r (MP a)	f _v (MP a)	f _{r+l} (MP a)
0	31.	37.	10.	10.0	4.2	2.4	0.7	1.2	0.	0.87	310	14	21	23.	22.	44.
1	82	40	01	7		0	9		71				2	7	2	1
0	31.	37.	10.	9.77	4.2	1.8	0.8	1	0.	0.87	300	11	18	23.	30.	47.
2	48	17	70		0		2		71				0	4	1	0
0	30.	38.	10.	9.77	4.3	2.1	1	1.30	0.	0.80	300	12	20.	22.	31.	47

3	01	30	19		0				7			.	0	7	2	
0	34.	34.	10.	9.00	4.3	2.2	0.8	1.2	0.	0.87	331	90.	12	22.	32	43.
4	47	70	08				8		7				2	8		1
0	31.	37.	10.	9.47	4	1.9	0.7	1.1	0.	0.87	299	19	24	23.	31.	47.
0	71	82	90				0		73			7	0	8	8	7
0	32.	30.	10.	9.43	4.3	2	0.9	1.2	0.	0.87	310	11	20.	22.	32.	44.
6	27	93	37		2		1		79			0	.	7	1	7
0	41.	29.	18.4	11.0	3.8	2.1	0.8	1.22	0.	0.89	279	13	20.	22	31.	47
7	17	41	0	4	0	4	4		77			.	.	22	23	
0	37.	32.	9.4	10.1	4.3	2.1	0.7	1.30	0.	0.87	342	11	19	22.	28.	47
8	0.3	29	3	9	8	3	2		43			.	.	2	9	
0	41.	29.	7.7	13.2	2.4	2.2	0.8	2.2	0.	0.88	277	10.	18	21.	30.	47.
9	08	20	7	8	3	9	4		4			.	.	7	30.	7
6	41.	30.	7.4	10.9	2.8	2.2	0.7	1.8	0.	0.88	274	18	30.	21.	30.	47.
.	41	71	4	2		8	2		4			.	.	2	1	1
6	02.	21.	00	17.0	3.2	20	0.8	1.0	0.	0.9	320	14	24	24.	33.	47.
1	94	93	9	4	7	1	4		11			0	.	0	2	8
6	47.	27.	3.4	100	3	1.8	0.9	0.87	0.	0.89	338	14	24	20.	33.	48.
2	13	31	7	9	3	7	0		30				.	0	7	7
6	04.	17.	0.4	100	2.7	1.9	1	0.98	0.	0.92	344	12	19	24.	34	47.
3	70	32	3	9	1	2			18				.	7	34	2
6	42.	31.	2.7	10.7	3.3	20	0.7	0.83	0.	0.87	301	13	20.	24	34.	49.
4	09	89	7	.	3	3	7		32			0	.	24	2	8
6	00.	21.	3.4	14.8	2.7	20	0.9	1	0.	0.91	301	12	18	27.	30.	49.
0	80	73	2	4	1	2			47			.	.	2	0	7
6	01.	24.	.	17.7	3.7	1.8	0.9	1.04	0.	0.89	388	70.	18	20.	32.	49.
6	22	08	.	7	2	7			29				.	3	0	0
6	78.	0.4	-	14.9	0.2	1.9	0.8	0.81	0.	0.91	389	90.	18	27.	34.	49.
7	81	7	70	7	0	8	4		47				.	3	4	0
6	00.	17.	3.1	100	2.7	1.9	0.8	1.13	0.	0.93	344	12	22	24.	32.	00.
8	74	00	7	9	2	7	9		34				.	0	7	00.
6	49.	22.	2.1	14.9	2.7	2	0.8	2.19	0.	0.9	300	90.	27	20	34.	47.
9	90	30	7	7	2	2	9		47				.	20	4	0
7	03.	20.	0.7	10.8	2.8	20	0.9	0.91	0.	0.91	324	13	24	24.	34.	49
.	34	88	4	2	1	7			47			.	0	0	7	
7	07.	17.	0.8	10.7	2.7	1.9	0.7	1.37	0.	0.92	377	18	29	20.	33	47.
1	04	04	.	.		0	2		47				.	3	33	73
7	48.	20.	2.9	10.4	2.9	20	0.7	0.70	0.	0.89	347	90.	18	24.	31.	49.
2	33	00	.	0	2	4	7		03				.	0	1	4
7	01.	21.	1.8	10.7	2.7	20	0.7	1.2	0.	0.91	329	90.	18	20.	33	47.
3	77	22	8	7	2	1	7		40				.	7	33	0
7	08.	17.	.	17.0	2.4	1.9	0.8	1.18	0.	0.93	334	12	18	20.	34.	48.
4	79	21	.	0	7	2	4		0				.	2	7	0
7	47.	28.	1.8	17.7	2.4	20	1	1.03	0.	0.88	347	14	19	24.	30.	47.
0	21	09	.	7	2	0			43				.	4	7	9

Continue Table (A-4)

No	C _r S %	C _v S %	C _r A %	C _v A %	Mg O%	SO _r %	Free Ca O%	L.O.I %	IR %	L.S.F %	S _s (Blaine) (m ² /kg)	IST (min)	FS T (min)	f _r (MP a)	f _v (MP a)	f _{rA} (MP a)
77	48.	28.	00	17.7	1.7	2.1	0.7	1	.	0.87	340	12	18	23.	27.	47

	۳۳	۱۰	۰	۷		۳	۸		۰۸			۰	۰	۹	۷		
۷۷	۰۴. ۷۷	۲۱. ۲۹	۰.۶ ۲	۱۶. ۳	۱.۴ ۳	۲.۱ ۸	۰.۸ ۴	۱.۲۰	۰. ۴۶	۰.۹۱	۳۱.	۱۱ ۰	۱۶ ۰	۲۰	۳۴. ۶۰	۴۹. ۳	
۷۸	۴۰. ۴۳	۲۹. ۶۰	۲.۰ ۸	۱۴.۶ ۰	۱.۹ ۰	۲	۰.۸ ۹	۱	۰. ۴۹	۰.۸۸	۳۲.	۹.	۱۰ ۰	۲۴. ۱	۳۱. ۳	۴۸. ۶	
۷۹	۴۴. ۰۲	۲۹. ۴۸	۳.۲ ۲	۱۰.۲ ۱	۱.۸ ۱	۲.۱ ۱	۰.۹ ۰	۱.۱	۰. ۷۲	۰.۸۸	۳۰.۱	۹.	۱۶ ۰	۲۰	۳۱	۴۷. ۳	
۸۰	۴۰. ۷۲	۲۸. ۳۸	۳.۴ ۷	۱۰. ۹	۱.۷ ۸	۲.۲ ۶	۰.۸ ۴	۰.۹۸	۰. ۴۰	۰.۸۸	۳۰.۰	۷.	۱۸ ۰	۲۴. ۰	۳۰.	۴۸. ۰	
۸۱	۰۷. ۱۹	۱۸. ۷۴	۲.۳ ۲	۱۴.۳ ۶	۱.۴ ۶	۲.۱	۰.۷ ۸	۱.۱۱	۰. ۶۸	۰.۹۲	۳۰.۱ ۰	۱۲ ۰	۱۸ ۰	۲۴. ۳۴	۳۳. ۸	۴۷. ۴	
۸۲	۰۴. ۰۴	۲۱. ۱۲	۰.۲ ۹	۱۰.۸ ۲	۱.۴ ۱	۱.۹ ۳	۰.۷ ۲	۱.۹	۰. ۳۶	۰.۹	۲۸۷. ۰	۱۳ ۰	۲۲ ۰	۲۴. ۳	۳۰.	۴۷. ۹	
۸۳	۰۰. ۸۲	۱۷. ۲۰	۲.۷ ۸	۱۰.۰ ۸	۱.۳ ۹	۲.۱ ۱	۰.۷ ۸	۲	۰. ۶۱	۰.۹۳	۲۸.	۱۹ ۰	۳۱ ۰	۲۰. ۰	۳۲. ۲	۴۹. ۲	
۸۴	۴۹. ۲۱	۲۳. ۸۸	۳.۴ ۷	۱۰.۰ ۸	۱.۶ ۶	۱.۹ ۷	۰.۷ ۲	۱.۶	۰. ۴۲	۰.۹	۳۲۴. ۷	۱۲ ۰	۲۴ ۰	۲۳. ۸	۳۱. ۲	۴۷. ۴۱	
۸۵	۰۰. ۴۸	۲۱. ۹۴	۳.۴ ۳	۱۰.۴ ۰	۱.۴ ۰	۲.۱ ۳	۰.۸ ۴	۱.۹۲	۰. ۶۰	۰.۹۱	۳۲۴. ۷	۱۶ ۰	۲۸ ۰	۲۴. ۳	۳۲. ۹	۴۷. ۰	
۸۶	۴۴. ۰۰	۳۱. ۴۰	۱.۰ ۶	۱۶.۴ ۳	۲.۱	۲.۰ ۹	۰.۷ ۸	۰.۸۰	۰. ۴۱	۰.۸۶	۳۱.	۱۹ ۰	۲۸ ۰	۲۴. ۶	۳۳	۴۹. ۰	
۸۷	۰۰. ۲۸	۲۳. ۴۷	۳.۳ ۳	۱۰.۲ ۱	۱.۶ ۱	۲.۱	۰.۷ ۸	۱.۴	۰. ۶۸	۰.۹	۳۲۲	۱۲ ۰	۱۸ ۰	۲۴. ۱	۳۴. ۴	۴۷. ۴	
۸۸	۰۸. ۰۹	۱۴. ۳۷	۰.۱ ۰	۱۲.۶ ۰	۱.۳ ۷	۱.۹	۰.۸ ۹	۱.۰۱	۰. ۰۷	۰.۹۴	۳۰۶	۱۳ ۰	۲۱ ۰	۲۰. ۰	۳۰. ۰	۰۰.	
۸۹	۴۶. ۷۱	۲۹. ۶۷	۰.۹ ۳	۱۶.۴ ۳	۲.۶	۱.۹ ۳	۰.۷ ۶	۰.۷۱	۰. ۳۳	۰.۸۷	۳۰.	۱۱ ۰	۱۷ ۶	۲۳. ۹	۳۳. ۰	۴۹. ۰	
۹۰	۰۷. ۴۳	۱۴. ۸۳	۲.۰ ۸	۱۰.۰ ۱	۱.۳	۱.۹ ۶	۱	۱.۳	۰. ۳۹	۰.۹۱	۳۱. ۰	۱۶ ۰	۲۰ ۰	۲۳. ۸	۳۰. ۸	۴۷	
۹۱	۴۴. ۶۷	۲۹. ۳۶	۲.۶ ۹	۱۰.۲ ۱	۲.۰	۲	۰.۹ ۲	۱.۳۰	۰. ۴۳	۰.۸۸	۳۲۲	۱۱ ۰	۱۷ ۰	۲۳. ۶۶	۳۲. ۱	۴۶. ۴	
۹۲	۰۴. ۹۹	۲۱. ۲۳	۰.۶ ۲	۱۶. ۳	۱.۰	۱.۹ ۱	۰.۹	۱	۰. ۱۹	۰.۹	۳۴۰.	۱۲ ۰	۲۴ ۰	۲۴. ۴۴	۳۱. ۸	۴۶. ۲	
۹۳	۰۱. ۸۷	۲۲. ۰۰	۱.۷ ۱	۱۰.۴ ۰	۱.۶ ۳	۲.۰ ۱	۰.۸	۱.۰	۰. ۴۷	۰.۹	۳۴۰	۱۲ ۰	۲۴ ۰	۲۴. ۹	۳۳. ۸	۴۸. ۰	
۹۴	۰۴. ۳۳	۲۲. ۸۰	۰.۲ ۱	۱۰.۰ ۸	۱.۹	۱.۹ ۹	۱.۱	۱.۲	۰. ۳۰	۰.۹	۳۳۰	۱۳ ۰	۲۰ ۰	۲۳. ۷	۳۱	۴۴. ۶	
۹۵	۴۴. ۲۰	۲۸. ۷۹	۲.۴ ۹	۱۰.۴ ۸	۲.۳	۱.۹ ۸	۰.۷ ۱	۰.۹	۰. ۴۸	۰.۸۷	۳۴۲	۱۴ ۰	۲۰ ۰	۲۴	۳۳	۴۹. ۱	
۹۶	۰۰. ۷۰	۲۱. ۳۷	۲.۲ ۲	۱۰. ۶	۱.۴ ۲	۱.۹ ۶	۰.۷ ۰	۱.۲	۰. ۰۰	۰.۹۱	۳۳۳	۱۰ ۰	۱۶ ۰	۲۴. ۷	۳۱	۴۹. ۲	
۹۷	۰۴. ۶۷	۲۱. ۰۲	۰.۱ ۷	۱۷. ۴	۱.۴	۱.۹	۰.۸ ۲	۰.۹	۰. ۱۲	۰.۹	۳۲۰	۱۷ ۰	۲۶ ۰	۲۴. ۶	۳۲	۰۰. ۷	
۹۸	۰۷. ۶۶	۱۷. ۳۰	۰.۴ ۱	۱۰.۲ ۱	۱.۲ ۳	۱.۹ ۰	۰.۶ ۹	۱	۰. ۴۰	۰.۹۲	۳۴۲	۱۰ ۰	۲۶ ۰	۲۰. ۱	۳۳. ۲	۰۰. ۸	
۹۹	۰۱. ۷۰	۲۲. ۳۰	۱.۶ ۷	۱۰.۰ ۱	۱.۷ ۰	۲.۱	۰.۸ ۹	۱.۴	۰. ۰	۰.۹	۳۰.	۱۲ ۰	۲۳ ۰	۲۴. ۸	۳۲. ۱	۴۸. ۲	
۱۰۰	۰۲. ۰۱	۲۰. ۸۷	۱.۴ ۱	۱۰.۰ ۱	۱.۳ ۰	۱.۹ ۸	۰.۸ ۰	۱.۱	۰. ۴۶	۰.۹۱	۳۳.	۱۰ ۰	۲۶ ۰	۲۴. ۹	۳۳. ۹	۴۸. ۷	

By applying eq. (۴-۱۲) on:

۱. The first model (i.e. eq. (۴-۰)):

$$\frac{\partial f_{(t)1}}{\partial SO_3} = 0$$

$$a_1 * a_2 * t * SO_3^{a_2 * t - 1} + a_5 C_3 S^{a_6 * t} + a_7 C_2 S^{a_8 * t} + a_9 (C_3 A + 1)^{a_{10} * t} + a_{11} C_4 AF^{a_{12} * t} = 0$$

$$\text{O.G.C} (SO_3 \%) = -\frac{1}{a_1 * a_2 * t} * (a_5 C_3 S^{a_6 * t} + a_7 C_2 S^{a_8 * t} + a_9 (C_3 A + 1)^{a_{10} * t} + a_{11} C_4 AF^{a_{12} * t})^{1/(a_2 * t - 1)} \quad \dots(\text{B-1})$$

$$\text{And: } \frac{\partial^2 f_{(t)1}}{\partial SO_3^2} < 0, \text{ so: } a_1 * a_2 * t * (a_2 * t - 1) * SO_3^{(a_2 * t - 2)} < 0 \quad \dots(\text{B-2})$$

By substituting the values of the coefficients:

$$\text{O.G.C} (SO_3 \%) = -\frac{1}{7.9052 * 0.0053 * t} * (6.145 C_3 S^{0.0016 * t} - 1.2724 C_2 S^{0.0017 * t} - 21.2644 (C_3 A + 1)^{-0.0006 * t} + 13.9798 C_4 AF^{0.0033 * t})^{1/(0.0053 * t - 1)} \quad \dots(\text{B-3})$$

$$7.9052 * 0.0053 * t * (0.0053 * t - 1) * SO_3^{(0.0053 * t - 2)} < 0 \quad \dots(\text{B-4})$$

2. The second model (i.e. eq. (4-6)):

$$\frac{\partial f_{(t)2}}{\partial SO_3} = 0$$

$$a_1 * a_2 * t * SO_3^{a_2 * t - 1} + a_3 S_s^{a_4 * t} + a_5 C_3 S^{a_6 * t} + a_7 C_2 S^{a_8 * t} + a_9 (C_3 A + 1)^{a_{10} * t} + a_{11} C_4 AF^{a_{12} * t} = 0$$

$$\text{O.G.C}(\text{SO}_3\%) = -\frac{1}{a_1 * a_2 * t} * (a_3 S_s^{a_4 * t} + a_5 C_3 S^{a_6 * t} + a_7 C_2 S^{a_8 * t} + a_9 (C_3 A + 1)^{a_{10} * t} + a_{11} C_4 A F^{a_{12} * t})^{1/(a_2 * t - 1)} \quad \dots(\text{B-5})$$

$$\text{And: } \frac{\partial^2 f_{(t)2}}{\partial SO_3^2} < 0, \text{ so: } a_1 * a_2 * t * (a_2 * t - 1) * SO_r^{(a_2 * t - 2)} < 0 \quad \dots(\text{B-6})$$

By substituting the values of the coefficients:

$$\text{O.G.C}(\text{SO}_3\%) = -\frac{1}{28.2396 * 0.0130 * t} * (-7.9462 S_s^{0.0046t} + 9.4217 C_3 S^{0.0042t} - 4.3184 C_2 S^{-0.0243t} - 45.6737 (C_3 A + 1)^{-0.0008t} + 36.9563 C_4 A F^{0.0019t})^{1/(0.013t - 1)} \quad \dots(\text{B-7})$$

$$28.2396 * 0.0130 * t * (0.0130 * t - 1) * SO_r^{(0.0130 * t - 2)} < 0 \quad \dots(\text{B-8})$$

3. The third model (i.e. eq. (4-7)):

$$\frac{\partial f_{(t)3}}{\partial SO_3} = 0$$

$$a_1 * a_2 * t * SO_3^{a_2 * t - 1} + a_3 S_s^{a_4 * t} + a_5 C_3 S^{a_6 * t} + a_7 C_2 S^{a_8 * t} + a_9 (C_3 A + 1)^{a_{10} * t} + a_{11} C_4 A F^{a_{12} * t} + a_{13} \text{MgO}^{a_{14} * t} + a_{15} \text{Free CaO}^{a_{16} * t} + a_{27} \text{Unsoundnes s}^{2 * a_{28} * t} = 0$$

$$\text{O.G.C}(\text{SO}_3\%) = -\frac{1}{a_1 * a_2 * t} * (a_3 S_s^{a_4 * t} + a_5 C_3 S^{a_6 * t} + a_7 C_2 S^{a_8 * t} + a_9 (C_3 A + 1)^{a_{10} * t} + a_{11} C_4 A F^{a_{12} * t} + a_{13} \text{MgO}^{a_{14} * t} + a_{15} \text{Free CaO}^{a_{16} * t} + a_{27} \text{Unsoundnes s}^{2 * a_{28} * t})^{1/(a_2 * t - 1)} \quad \dots(\text{B-9})$$

$$\text{And: } \frac{\partial^2 f_{(t)3}}{\partial SO_3^2} < 0, \text{ so: } a_1 * a_2 * t * (a_2 * t - 1) * SO_r^{(a_2 * t - 2)} < 0 \quad \dots(\text{B-10})$$

By substituting the values of the coefficients:

$$\begin{aligned} \text{O.G.C}(\text{SO}_3\%) = & -\frac{1}{-36.2959 * -0.5293 * t} * (-8.8811\text{S}_s^{-0.0014t} + 9.6260\text{C}_3\text{S}^{-0.0009t} \\ & - 0.0033\text{C}_2\text{S}^{0.0278t} + 0.1373(\text{C}_3\text{A} + 1)^{-0.2905t} + 21.4302\text{C}_4\text{AF}^{0.0021t} \\ & - 0.1206\text{MgO}^{0.0071t} - 25.5663\text{FreeCaO}^{0.00008t} - \\ & 0.000003\text{Unsoundness}^{2 * -0.0694t})^{1/(-0.5293t-1)} \quad \dots(\text{B} - 11) \end{aligned}$$

$$-36.2959 * -0.5293 * t * (-0.5293t - 1) * \text{SO}_3^{(-0.5293t-2)} < 0 \quad \dots(\text{B}-12)$$

ξ. The forth model (i.e. eq. (ξ-Λ)):

$$\frac{\partial f_{(t)4}}{\partial \text{SO}_3} = 0$$

$$\begin{aligned} & a_1 * a_2 t * \text{SO}_3^{a_2 t - 1} + a_3 \text{S}_s^{a_4 t} + a_5 \text{C}_3 \text{S}^{a_6 t} + a_7 \text{C}_2 \text{S}^{a_8 t} + a_9 (\text{C}_3 \text{A} + 1)^{a_{10} t} + a_{11} \text{C}_4 \text{AF}^{a_{12} t} \\ & + a_{13} \text{MgO}^{a_{14} t} + a_{15} \text{Free CaO}^{a_{16} t} + a_{17} \text{LOI}^{a_{18} t} + a_{19} \text{IR}^{a_{20} t} + a_{21} \text{LSF}^{a_{22} t} + a_{23} \text{SM}^{a_{24} t} \\ & + a_{25} \text{AR}^{a_{26} t} + a_{27} \text{Unsoundness}^{2 a_{28} t} = 0 \end{aligned}$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3\%) = & -\frac{1}{a_1 * a_2 * t} * (a_3 \text{S}_s^{a_4 t} + a_5 \text{C}_3 \text{S}^{a_6 t} + a_7 \text{C}_2 \text{S}^{a_8 t} + a_9 (\text{C}_3 \text{A} + 1)^{a_{10} t} \\ & + a_{11} \text{C}_4 \text{AF}^{a_{12} t} + a_{13} \text{MgO}^{a_{14} t} + a_{15} \text{FreeCaO}^{a_{16} t} + a_{17} \text{LOI}^{a_{18} t} + \\ & a_{19} \text{IR}^{a_{20} t} + a_{21} \text{LSF}^{a_{22} t} + a_{23} \text{SM}^{a_{24} t} + a_{25} \text{AR}^{a_{26} t} + \\ & a_{27} \text{Unsoundness}^{2 a_{28} t})^{1/(a_2 t - 1)} \quad \dots(\text{B} - 13) \end{aligned}$$

$$\text{And: } \frac{\partial^2 f_{(t)4}}{\partial SO_3^2} < 0, \text{ so: } a_1 * a_2 * (a_2 - 1) * SO_3^{(a_2 - 2)} < 0, \quad \dots(\text{B-14})$$

By substituting the values of the coefficients:

$$\begin{aligned} \text{O.G.C}(SO_3 \%) = & -\frac{1}{21.4776 * 0.0168 * t} * (1.4555 S_s^{0.0050t} + 1.4231 C_3 S^{0.0088t} \\ & + 0.0060 C_2 S^{0.0215t} - 1.8939 (C_3 A + 1)^{0.0123t} - 0.1260 C_4 A F^{0.0258t} \\ & - 0.1929 MgO^{0.0316t} - 2.4026 \text{FreeCaO}^{0.0021t} + 0.00007 LOI^{0.0967t} \\ & + 0.1305 IR^{-0.0266t} - 13.9161 LSF^{3.0387t} - 1.2097 SM^{0.0376t} + \\ & 5.6733 AR^{0.0016t} - 0.8008 \text{Unsoundness}^{2 * -0.0005t})^{1/(0.0168t - 1)} \quad \dots(\text{B-15}) \end{aligned}$$

$$21.4776 * 0.0168 * t * (1.4555 S_s^{0.0050t} + 1.4231 C_3 S^{0.0088t} + \dots) < 0, \quad \dots(\text{B-16})$$

By applying eq. (B-16) on:

o. The model (i.e. eq. (B-15)):

$$\text{, so: } \frac{\partial f_{(t)5}}{\partial SO_3} = 0$$

$$a_1 * a_2 * SO_3^{a_2 - 1} + a_5 C_3 S^{a_6} + a_7 C_2 S^{a_8} + a_9 (C_3 A + 1)^{a_{10}} + a_{11} C_4 A F^{a_{12}} = 0$$

$$\text{And: } \text{O.G.C}(SO_3 \%) = -\frac{1}{a_1 * a_2} * (a_5 C_3 S^{a_6} + a_7 C_2 S^{a_8} + a_9 (C_3 A + 1)^{a_{10}} + a_{11} C_4 A F^{a_{12}})^{1/(a_2 - 1)} \quad \dots(\text{C-1})$$

$$\frac{\partial f_{(t)1}}{\partial SO_3} = 0, \text{ so: } a_1 * a_2 * (a_2 - 1) * SO_3^{(a_2 - 2)} < 0, \quad \dots(\text{C-2})$$

By substituting the values of the coefficients at each age:

$$\text{O.G.C (SO}_3\text{ \%)}_{\text{at3Days}} = -\frac{1}{-0.6768 * 2.7080} * (1.8642C_3S^{-0.3206} + 1.4159C_2S^{0.3852} + 1.6503(C_3A + 1)^{0.2101} + 1.0298C_4AF^{-0.2069})^{1/(2.7080-1)} \dots(\text{C - 3})$$

$$-0.6768 * 2.7080 * (2.7080 - 1) * \text{SO}_r^{(2.7080 - 2)} < 0 \dots(\text{C-4})$$

$$\text{O.G.C (SO}_3\text{ \%)}_{\text{at7Days}} = -\frac{1}{-0.7965 * 2.4351} * (1.4275C_3S^{-0.3734} + 0.4947C_2S^{0.5968} + 1.4078(C_3A + 1)^{0.4715} + 1.6060C_4AF^{-0.6086})^{1/(2.4351-1)} \dots(\text{C - 5})$$

$$-0.7965 * 2.4351 * (2.4351 - 1) * \text{SO}_r^{(2.4351 - 2)} < 0 \dots(\text{C-6})$$

$$\text{O.G.C (SO}_3\text{ \%)}_{\text{at28Days}} = -\frac{1}{-0.4880 * 3.1022} * (1.8022C_3S^{-0.2076} + 3.7018C_2S^{0.2052} + 2.8846(C_3A + 1)^{0.1788} + 5.3879C_4AF^{-0.2671})^{1/(3.1022-1)} \dots(\text{C - 7})$$

$$-0.4880 * 3.1022 * (3.1022 - 1) * \text{SO}_r^{(3.1022 - 2)} < 0 \dots(\text{C-8})$$

$$\text{O.G.C (SO}_3\text{ \%)}_{\text{at60Days}} = -\frac{1}{-0.6970 * 2.6179} * (2.2061C_3S^{-0.3807} + 2.6893C_2S^{0.2381} + 0.6574(C_3A + 1)^{0.7889} + 1.8608C_4AF^{-0.1626})^{1/(2.6179-1)} \dots(\text{C - 9})$$

$$-0.6970 * 2.6179 * (2.6179 - 1) * \text{SO}_r^{(2.6179 - 2)} < 0 \dots(\text{C-10})$$

6. The model Ψ *(i.e. eq. (4-18)):

$$, \text{ so: } \frac{\partial f_{(t)2}^*}{\partial SO_3} = 0$$

$$a_1 * a_2 * SO_3^{a_2-1} + a_3 S_s^{a_4} + a_5 C_3 S^{a_6} + a_7 C_2 S^{a_8} + a_9 (C_3 A + 1)^{a_{10}} + a_{11} C_4 A F^{a_{12}} = 0$$

$$\text{O.G.C}(SO_3 \%) = -\frac{1}{a_1 * a_2} * (a_3 S_s^{a_4} + a_5 C_3 S^{a_6} + a_7 C_2 S^{a_8} + a_9 (C_3 A + 1)^{a_{10}} + a_{11} C_4 A F^{a_{12}})^{1/(a_2-1)} \quad \dots(\text{C-11})$$

And:

$$\frac{\partial f_{(t)2}^*}{\partial SO_3} = 0 \quad , \text{ so: } a_1 * a_2 * (a_2 - 1) * SO_3^{(a_2 - 2)} < 0 \quad \dots(\text{C-12})$$

By substituting the values of the coefficients at each age:

$$\text{O.G.C}(SO_3 \%)_{\text{at3Days}} = -\frac{1}{-0.7597 * 2.5926} * (2.1347 S_s^{0.1227} + 1.2996 C_3 S^{-0.3884} + 1.1643 C_2 S^{0.2522} + 0.2662 (C_3 A + 1)^{0.2109} + 1.6896 C_4 A F^{-0.2477})^{1/(2.5926-1)} \quad \dots(\text{C-13})$$

$$-1.7097 * 2.0926 * (2.0926 - 1) * SO_3^{(2.0926-2)} < 0 \quad \dots(\text{C-14})$$

$$\text{O.G.C}(SO_3 \%)_{\text{at7Days}} = -\frac{1}{-1.2369 * 2.1732} * (1.1152 S_s^{0.2335} + 0.1293 C_3 S^{-0.7078} + 0.5757 C_2 S^{0.3501} + 1.3478 (C_3 A + 1)^{0.2157} + 2.0349 C_4 A F^{-0.2840})^{1/(2.1732-1)} \quad \dots(\text{C-15})$$

$$-1.2369 * 2.1732 * (2.1732 - 1) * SO_3^{(2.1732-2)} < 0 \quad \dots(\text{C-16})$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at28Days}} = & -\frac{1}{-0.5395 * 3.4073} * (0.3289\text{S}_s^{0.5105} + 1.5226\text{C}_3\text{S}^{0.2023} \\ & + 1.5952\text{C}_2\text{S}^{0.6167} + 1.2843(\text{C}_3\text{A} + 1)^{0.3571} + \\ & 0.6042\text{C}_4\text{AF}^{-0.1005})^{1/(3.4073-1)} \quad \dots(\text{C-17}) \end{aligned}$$

$$\dots 0.390 * 3.4073 * (3.4073 - 1) * \text{SO}_3^{(3.4073-2)} < 0 \quad \dots(\text{C-18})$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at60Days}} = & -\frac{1}{-0.8857 * 2.7479} * (2.1154\text{S}_s^{0.2516} + 1.4414\text{C}_3\text{S}^{-0.3666} \\ & + 1.2216\text{C}_2\text{S}^{0.3603} + 1.4243(\text{C}_3\text{A} + 1)^{0.3164} + \\ & 1.8734\text{C}_4\text{AF}^{-0.4939})^{1/(2.7479-1)} \quad \dots(\text{C-19}) \end{aligned}$$

$$\dots 1.8807 * 2.7479 * (2.7479 - 1) * \text{SO}_3^{(2.7479-2)} < 0 \quad \dots(\text{C-20})$$

V. The model Ψ^* (i.e. eq. (4-19)):

$$, \text{ so: } \frac{\partial f_{(t)3}^*}{\partial \text{SO}_3} = 0$$

$$\begin{aligned} a_1 * a_2 * \text{SO}_3^{a_2-1} + a_3\text{S}_s^{a_4} + a_5\text{C}_3\text{S}^{a_6} + a_7\text{C}_2\text{S}^{a_8} + a_9(\text{C}_3\text{A} + 1)^{a_{10}} + a_{11}\text{C}_4\text{AF}^{a_{12}} \\ + a_{13}\text{MgO}^{a_{14}} + a_{15}\text{Free CaO}^{a_{16}} + a_{27}\text{Unsoundnes } s^{2*a_{28}} = 0 \end{aligned}$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%) = & -\frac{1}{a_1 * a_2} * (a_3\text{S}_s^{a_4} + a_5\text{C}_3\text{S}^{a_6} + a_7\text{C}_2\text{S}^{a_8} + a_9(\text{C}_3\text{A} + 1)^{a_{10}} + \\ & a_{11}\text{C}_4\text{AF}^{a_{12}} + a_{13}\text{MgO}^{a_{14}} + a_{15}\text{FreeCaO}^{a_{16}} + \\ & a_{27}\text{Unsoundnes } s^{2*a_{28}})^{1/(a_2-1)} \quad \dots(\text{C-21}) \end{aligned}$$

And:

$$\frac{\partial^2 f_{(t)_3}}{\partial SO_3^2} < 0, \text{ so: } a_1 * a_r * (a_r - 1) * SO_r^{(a_2 - 1)} < 0 \quad \dots(C-22)$$

By substituting the values of the coefficients at each age:

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at3Days}} = & -\frac{1}{-0.3412 * 3.1358} * (1.1648S_s^{0.2456} + 0.3260C_3S^{0.6919} + \\ & 1.6595C_2S^{0.2457} + 0.3419(C_3A + 1)^{0.6264} + 0.2855C_4AF^{-0.5547} \\ & - 2.2853MgO^{0.1412} - 1.2178\text{FreeCaO}^{-0.0430} \\ & - 1.1918\text{Unsoundness}^{2 * -0.2064})^{1/(3.1358 - 1)} \quad \dots(C - 23) \end{aligned}$$

$$-0.3412 * 3.1358 * (3.1358 - 1) * SO_r^{(3.1358 - 1)} < 0 \quad \dots(C-24)$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at7Days}} = & -\frac{1}{-0.8092 * 2.7379} * (0.5346S_s^{0.4110} + 0.7569C_3S^{0.6723} + \\ & 1.5358C_2S^{-0.5191} + 0.5204(C_3A + 1)^{-1.7919} + 0.4179C_4AF^{0.8301} - \\ & 0.5834MgO^{-0.1074} - 3.3427\text{FreeCaO}^{0.0864} - \\ & 0.2490\text{Unsoundness}^{2 * -0.3253})^{1/(2.7379 - 1)} \quad \dots(C - 25) \end{aligned}$$

$$-0.8092 * 2.7379 * (2.7379 - 1) * SO_r^{(2.7379 - 1)} < 0 \quad \dots(C-26)$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at28Days}} = & -\frac{1}{-0.6697 * 2.7197} * (1.7152S_s^{0.2335} + 0.8388C_3S^{-0.4614} + \\ & 2.5044C_2S^{0.2968} + 1.5478(C_3A + 1)^{0.3088} + 0.7577C_4AF^{-0.8578} - \\ & 0.5457MgO^{0.2725} - 1.0835\text{FreeCaO}^{0.1062} - 1.0050 \\ & \text{Unsoundness}^{2 * -0.1913})^{1/(2.7197 - 1)} \quad \dots(C - 27) \end{aligned}$$

$$-0.6697 * 2.7197 * (2.7197 - 1) * SO_r^{(2.7197 - 1)} < 0 \quad \dots(C-28)$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3\%)_{\text{at60Days}} = & -\frac{1}{-0.6691 * 2.5249} * (0.6405\text{S}_s^{0.4821} + 0.7445\text{C}_3\text{S}^{-0.5309} \\ & + 3.6047\text{C}_2\text{S}^{-0.5315} + 1.8716(\text{C}_3\text{A} + 1)^{0.2087} + 4.2641\text{C}_4\text{AF}^{-0.3159} - \\ & 3.6047\text{MgO}^{-0.5315} - 0.5283\text{FreeCaO}^{0.3944} - \\ & 2.1306\text{Unsoundness}^{2*-0.2118})^{1/(2.5249-1)} \quad \dots(\text{C}-29) \end{aligned}$$

$$-0.6691 * 2.5249 * (2.5249 - 1) * \text{SO}_r^{(2.5249-2)} < 0, \quad \dots(\text{C}-30)$$

∧. The model ξ^* (i.e. eq. (ξ-20)):

$$, \text{ so: } \frac{\partial f_{(t)4}^*}{\partial \text{SO}_3} = 0$$

$$\begin{aligned} & a_1 * a_2 * \text{SO}_3^{a_2-1} + a_3\text{S}_s^{a_4} + a_5\text{C}_3\text{S}^{a_6} + a_7\text{C}_2\text{S}^{a_8} + a_9(\text{C}_3\text{A} + 1)^{a_{10}} + a_{11}\text{C}_4\text{AF}^{a_{12}} \\ & + a_{13}\text{MgO}^{a_{14}} + a_{15}\text{FreeCaO}^{a_{16}} + a_{17}\text{LOI}^{a_{18}} + a_{19}\text{IR}^{a_{20}} + a_{21}\text{LSF}^{a_{22}} + a_{23}\text{SM}^{a_{24}} \\ & + a_{25}\text{AR}^{a_{26}} + a_{27}\text{Unsoundness}^{2*a_{28}} = 0 \end{aligned}$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3\%) = & -\frac{1}{a_1 * a_2} * (a_3\text{S}_s^{a_4} + a_5\text{C}_3\text{S}^{a_6} + a_7\text{C}_2\text{S}^{a_8} + a_9(\text{C}_3\text{A} + 1)^{a_{10}} + \\ & a_{11}\text{C}_4\text{AF}^{a_{12}} + a_{13}\text{MgO}^{a_{14}} + a_{15}\text{FreeCaO}^{a_{16}} + a_{17}\text{LOI}^{a_{18}} + \\ & a_{19}\text{IR}^{a_{20}} + a_{21}\text{LSF}^{a_{22}} + a_{23}\text{SM}^{a_{24}} + a_{25}\text{AR}^{a_{26}} + \\ & a_{27}\text{Unsoundness}^{2*a_{28}})^{1/(a_2-1)} \quad \dots(\text{C}-31) \end{aligned}$$

And:

$$\frac{\partial^2 f_{(t)4}^*}{\partial \text{SO}_3^2} < 0, \text{ so: } a_1 * a_2 * (a_2 - 1) * \text{SO}_r^{(a_2-2)} < 0, \quad \dots(\text{C}-32)$$

By substituting of the values of the coefficients at each age:

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at3Days}} = & -\frac{1}{-0.6752 * 2.4879} * (0.7755S_s^{0.2962} + 1.2629C_3S^{0.3163} \\ & + 1.4071C_2S^{0.2182} + 1.1861(C_3A + 1)^{0.4309} + 1.1298C_4AF^{0.1534} - \\ & 0.6657MgO^{0.2877} - 1.6503FreeCaO^{0.7981} - 1.877LOI^{-0.3203} - \\ & 0.3659IR^{1.2307} - 1.4552LSF^{0.1985} - 0.1292SM^{-1.2500} - 0.1256AR^{-0.9656} \\ & - 0.6531Unsoundness^{2*-0.2190})^{1/(2.4879-1)} \quad \dots(\text{C-33}) \end{aligned}$$

$$\dots 0.6752 * 2.4879 * (2.4879 - 1) * SO_r^{(2.4879 - 1)} < \dots (\text{C-34})$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at7Days}} = & -\frac{1}{-0.7636 * 2.4136} * (0.8520S_s^{0.3360} + 1.0208C_3S^{0.3413} \\ & + 2.8463C_2S^{0.1362} + 1.8821(C_3A + 1)^{0.4017} + 0.5533C_4AF^{0.4425} - \\ & 0.1244MgO^{1.6660} - 0.7932FreeCaO^{0.2833} - 7.0813LOI^{-0.1199} - \\ & 0.1513IR^{0.3433} - 0.2566LSF^{-5.0293} - 4.6376SM^{-11.7035} - 0.4467AR^{-2.8008} \\ & - 1.1008Unsoundness^{2*-0.1808})^{1/(2.4136-1)} \quad \dots(\text{C-35}) \end{aligned}$$

$$\dots 0.7636 * 2.4136 * (2.4136 - 1) * SO_r^{(2.4136 - 1)} < \dots (\text{C-36})$$

$$\begin{aligned} \text{O.G.C}(\text{SO}_3 \%)_{\text{at28Days}} = & -\frac{1}{-0.6344 * 2.8106} * (2.2556S_s^{0.1676} + 1.4245C_3S^{0.3156} + \\ & 1.4643C_2S^{0.2536} + 1.2982(C_3A + 1)^{0.6077} + 1.3565C_4AF^{0.1788} - \\ & 0.7166MgO^{-1.7022} - 0.5442FreeCaO^{0.1256} - 0.3803LOI^{0.1731} - \\ & 0.6188IR^{0.1258} - 0.4476LSF^{2.4387} - 5.8126SM^{-27.6278} - 2.1976AR^{-0.0313} \\ & - 1.3229Unsoundness^{2*-0.2596})^{1/(2.8106-1)} \quad \dots(\text{C-37}) \end{aligned}$$

$$\dots 0.6344 * 2.8106 * (2.8106 - 1) * SO_r^{(2.8106 - 1)} < \dots (\text{C-38})$$

$$\begin{aligned}
\text{O.G.C}(\text{SO}_3 \%)_{\text{at60Days}} = & -\frac{1}{-0.6765 * 2.5980} * (1.8086\text{S}_s^{0.2468} + 1.0363\text{C}_3\text{S}^{0.3366} + \\
& 1.5802\text{C}_2\text{S}^{0.1282} + 2.0345(\text{C}_3\text{A} + 1)^{0.2954} + 1.1093\text{C}_4\text{AF}^{0.3310} - \\
& 0.3830\text{MgO}^{0.5265} - 0.5446\text{FreeCaO}^{-0.7690} - 3.7366\text{LOI}^{-0.3967} - \\
& 0.3379\text{IR}^{0.7027} - 0.2058\text{LSF}^{0.2279} - 0.7291\text{SM}^{-0.1866} - 1.9090\text{AR}^{-0.1905} \\
& - 1.4199\text{Unsoundness}^{2 * -0.1831})^{1/(2.598-1)} \quad \dots(\text{C}-39)
\end{aligned}$$

$$-0.6765 * 2.5980 * (2.5980 - 1) * \text{SO}_r^{(2.5980 - 1)} < 0 \quad \dots(\text{C}-40)$$